



CHARLESTON LIMEWASH LIMEPAINT APPLICATION

Our Limepaints have been created to compliment our Limewashes, and to provide an alternative for surfaces that aren't recommended for a traditional Limewash application. Our Limepaints contain an extra binder that allows the mixture to stick to most surfaces, including less permeable surfaces that won't absorb Limewash. Using Limepaint gives you the freedom to enjoy the look of Limewash on all surfaces.

Surfaces: Limepaint can be applied to interior & exterior:

- Masonry Surfaces -**
- Stucco
 - Brick
 - Stone
- Cement Board
 - Plaster

- Previously painted surfaces -**
- Acrylic paints & stains
 - Latex paints

Limepaint is not recommended for use over oil based paints & stains unless first treated with a universal primer.

Preparation: Before you begin, ensure that the surface is free of contaminants and loose debris. Prepare your painting area, and gather your safety materials.

IMPORTANT: Flaking or peeling may occur if painting over weak paint layers.

Coverage: 1 Pint of concentrate covers approximately 65-85 square feet.

Dilution: Limepaint is shipped in a concentrated putty form. The Limepaint putty received, should be mixed well, then diluted with 100% - 200% water, before application to your desired consistency for the effect that you are trying to achieve.

Concentrate	100% Water Dilution Makes	200% Water Dilution Makes
1 Pint	2 Pints	3 Pints
1 Quart	2 Quarts	3 Quarts
1 Gallon	2 Gallon	3 Gallons
2.5 Gallons	5 Gallons	7.5 Gallons
5 Gallons	10 Gallons	15 Gallons



CHARLESTON LIMEWASH LIMEPAINT APPLICATION

- Utilization:** **Unpainted Masonry Surfaces -**
1. **IMPORTANT:** Mix the Limepaint putty thoroughly (in original container provided) **BEFORE** diluting with water, according to the directions listed below.
 2. An all-purpose paint brush is recommended for use when applying Limepaint. For large exterior areas, a 4" or wider brush is recommended.
 3. **IMPORTANT: DO NOT USE A ROLLER OR SPONGE TO APPLY LIMEPAINT**
 4. Apply the Limepaint according to the application instructions listed below
 5. When applying Limepaint, a random brushstroke is recommended.
 6. Allow 24 hours of drying time between coats.
 7. Continue to apply the Limepaint in coats until you achieve your desired effect.
 - 1 coat - glaze / translucent finish
 - 2 coats - semi-opaque / semi-solid finish
 - 3 coats - opaque / solid finish

Previously Painted Surfaces - Universal primer is required!

1. If applying to a surface previously coated with an oil based paint or stain, first apply a universal primer. Let dry.
2. Mix the Limepaint thoroughly according to the mixing directions listed below.
3. An all-purpose paint brush is recommended for use when applying Limepaint. For large exterior areas, a 4" or wider brush is recommended.
4. **IMPORTANT: DO NOT USE A ROLLER OR SPONGE TO APPLY LIMEPAINT**
5. Apply the Limepaint according to the application instructions listed below
6. When applying Limepaint, a random brushstroke is recommended.
7. Allow 24 hours of drying time between coats.
8. Continue to apply the Limepaint in coats until you achieve your desired effect.
 - 1 coat - glaze / translucent finish
 - 2 coats - semi-opaque / semi-solid finish
 - 3 coats - opaque / solid finish

- Mixing:**
1. When mixing Limepaint, wear appropriate eye protection and gloves. Refer to the included SDS information sheet.
 2. **IMPORTANT:** Mix the Limepaint putty thoroughly (in original container provided) **BEFORE** diluting with water. A 5 gallon plastic bucket (available at any hardware/paint store) is recommended for mixing.
 3. Pour or scrape the Limepaint putty into your mixing bucket (a rubber spatula works well for this step).
 4. Dilute the Limepaint with 100%-200% water (1:1 - 1:2 ratio of putty:water) **IMPORTANT:** 100% water dilution is less transparent than 200% dilution, please mix accordingly. A test sample is recommended before application to achieve your desired effect.
 5. Thoroughly mix the putty and water. A paint mixer or electric drill is recommended for mixing, but a wooden paint stick may be used as well.



CHARLESTON LIMEWASH LIMEPAINT APPLICATION

- Application:** **Do not paint in temperatures below 50°F or heat in excess of 90°F.**
1. Pour a manageable amount of **thoroughly mixed**, diluted Limepaint into a smaller container to paint from. **IMPORTANT:** Be sure to stir the Limepaint regularly throughout the painting process.
 2. With an appropriately sized brush, apply the Limepaint using random cross hatched strokes. (for detailed step by step instructions, view our instructional video at www.limewash.com). For larger areas such as plastered sheet rock, brick, stucco, and painted walls any 4-6" all purpose paint brush is advised. For cutting around trim work on all surfaces, a 2.5" all-purpose edger brush is recommended. For smaller projects, and all purpose paint brush may be used. **Be sure to maintain a wet edge on your brush during application.**
 3. Allow 24 hours for the 1st coat to dry. As the Limepaint dries, it should lighten considerably,
 4. If desired add a 2nd coat.
 5. Allow an additional 24 hours of drying time between each coat. Continue to add additional coats until you have achieved your desired effect.
 - 1 coat - glaze / translucent finish
 - 2 coats - semi-opaque / semi-solid finish
 - 3 coats - opaque / solid finish

Clean Up: Limepaint should be cleaned with water. Use a mild acid (vinegar) solution to remove dried Limepaint.

Contact: Charleston Limewash
4221 Rivers Ave., Suite E
Charleston, SC 29405
Tel: +1.843.793.2009
www.limewash.com
info@limewash.com

Disclaimer: The information included in these information and technical data sheets - whether verbal or written - is for guidance only, without warranty and does not replace the use of common sense and experience. Since individual site and application conditions are beyond our control, we accept no liability for the performance of the product, beyond the value of the goods delivered by us. Any colors must be verified by the user prior to application.