

27TMX DATA SHEET for Renewable Energy and Backup Power Applications

SIGNATURE LINE

- DIMENSIONS: inches (mm)
- **BATTERY:** Flooded/wet lead-acid battery
- **COLOR:** Maroon (case/cover)
- MATERIAL: Polypropylene



PRODUCT SPECIFICATIONS

BCI GROUP SIZE	ТҮРЕ	CAPACITY ^A Amp-Hours (AH)							ENERGY (kWh)	VOLTAGE	TERMINAL	DIMENSIONS [®] Inches (mm)			WEIGHT lbs.
		2-Hr Rate	5-Hr Rate	10-Hr Rate	20-Hr Rate	48-Hr Rate	72-Hr Rate	100-Hr Rate	100-Hr Rate	VULIAGE	Type ^D **	Length	Width	Height ^c	(kg)
SIGNATURE LINE - DEEP-CYCLE FLOODED BATTERIES															
27	27TMX	68	85	97	105	112	114	117	1.40	12 VOLT	5	12-3/4 (324)	6-3/4 (171)	9-3/4 (248)	55 (25)

CHARGING INSTRUCTIONS

CHARGER VOLTAGE SETTINGS (AT 77°F/25°C)					
	Voltage per cell				
Absorption charge	2.35-2.45				
Float charge	2.20				
Equalize charge	2.58				

Do not install or charge batteries in a sealed or non-ventilated compartment. Constant under or overcharging will damage the battery and shorten its life as with any battery.

OPERATIONAL DATA

Operating Temperature	Specific Gravity
-4°F to 113°F (-20°C to +45°C). At temperatures below $32°F$ (0°C) maintain a state of charge greater than 60%.	The specific gravity at 100% state-of-charge is 1.280


CHARGING TEMPERATURE COMPENSATION

To the Voltage Reading -- Subtract 0.005 volt per cell (VPC) for every 1°C above 25°C or add 0.005 volt per cell for every 1°C below 25°C.

EXPECTED LIFE VS. TEMPERATURE

Chemical reactions internal to the battery are driven by voltage and temperature. The higher the battery temperature, the faster chemical reactions will occur. While higher temperatures can provide improved discharge performance the increased rate of chemical reactions will result in a corresponding loss of battery life. As a rule of thumb, for every 10°C increase in temperature the reaction rate doubles. Thus, a month of operation at 35°C is equivalent in battery life to two months at 25°C. Heat is an enemy of all lead acid batteries, FLA, AGM and gel alike and even small increases in temperature will have a major influence on battery life.

TERMINAL CONFIGURATIONS



Made in the USA

A. The amount of amp-hours (AH) a battery can deliver when discharged at a constant rate at 77°F (25°C) and maintain a voltage above 1.75 V/cell. Capacities are based on peak performance.

B. Dimensions are based on nominal size. Dimensions may vary depending on type of handle or terminal.


C. Dimensions taken from bottom of the battery to the highest point on the battery. Heights may vary depending on type of terminal.

D. Terminal images are representative only. Trojan's Battery testing procedures adhere to both BCI and IEC test standards.


Additional Terminals Available

27TMX DATA SHEET for Renewable Energy and Backup Power Applications

SIGNATURE LINE




TROJAN 27TMX PERFORMANCE




PERCENT CAPACITY VS. TEMPERATURE

6-3/4 (171) Width



TYPICAL CYCLE LIFE IN A STATIONARY APPLICATION





Trojan batteries are available worldwide. We offer outstanding technical support, provided by full-time application engineers.

call 800.423.6569 or + 1.562.236.3000 or visit www.trojanbatteryRE.com

12380 Clark Street, Santa Fe Springs, CA 90670 • USA or email re@trojanbattery.com

TRJN_27TMX •DS_0113

© 2013 Trojan Battery Company. All rights reserved. Trojan Battery Company is not liable for damages that may result from any information provided in or omitted from this publication, under any circumstances. Trojan Battery Company reserves the right to make adjustments to this publication at any time, without notices or obligation. Please check the Trojan Battery website (www.trojanbattery.com) for the most up-to-date information.