ortofon microtech

Precision engineering innovation

PRODUCT DATA SHEET OM 1133

Properties	Unit		Test method	Values
Rubber type Colour				BIIR Blue
Hardness	Sh A		ISO 7619-1	48 ±5
Tensile strength	MPa		ISO 37	4.0
Elongation at break	%		ISO 37	650
Density	g/cm ³			1.38 ±0.02
Range of temperature in dry air	°C			-10 to +140
Compression set, small, 24h/70°C	%		ISO 815	28
Wear resistance				••
Resistance to weather and ozone				••
Resistance to hydrolysis (water and steam)				••
Resistance to chemicals (acids/bases)				••
Resistance to mineral oil and gas				•
				Scale: Very poor Poor Average Good Very good
Special properties		Applications		
High impermeability to gases and liquids Excellent aging stability Very good heat resistance Good damping properties		Dampers Tubes Membranes Antivibration mounting Medical industry		

Caution

Abovementioned results are based on laboratory tests and must be evaluated for the specific articles and applications.

Fire may create small amounts of hydrogen sulfide and carbon dioxide. Disposal by incineration in compliance with local regulations.

© Ortofon A/S. All Rights Reserved.

July 2016