

Properties	Unit	Test method	Values
Polymer base			SEBS
Colour			Black
Hardness	Sh A	ISO 868 (3s)	15
Tensile strength	MPa	ISO 37	↓1,5 ↔4,0
Elongation at break	%	ISO 37	↓750 ↔900
Density	g/cm3	ISO 1183-1	1,9
Tear resistance	N/mm	ISO 34-2	↓12 ↔16
Compression Set 22hr/70°C	%	ISO 815	30
Tensile modulus at 100% elongation	MPa	ISO 37	↓0,6 ↔0,5
Tensile modulus at 200% elongation	MPa	ISO 37	↓0,8 ↔0,7
Tensile modulus at 300% elongation	MPa	ISO 37	↓1,1 ↔1,0

Special properties

Adhesion to PP

Applications

Universal

Caution

All values reported are typical values based on sample laboratory tests and are not a guarantee of performance. The responsibility to conduct testing to determine suitability of use for the particular process or end-use application remains with the customer.

Fire may create small amounts of hydrogen sulfide and carbon dioxide. Disposal by incineration in compliance with local regulations.