



Technical Data Sheet

Aggregate Name: Silver Pearl Quartz

Sizes Available: 1-3mm, 2-5mm

Material: Quartz

Product Description: Pale grey aggregate, angular in shape



Technical Information

Tested in accordance with BS EN 1097-2: 2010 - Annex B

LA Abrasion = 36

Tested in accordance with BS EN 1097-6: 2013 - Clause 8

Particle density on an oven-dried basis = 2.48 Mg/m³

Particle density on a saturated and surface-dried basis = 2.53 Mg/m³

Apparent Particle density = 2.62 Mg/m³

Water absorption (of dry mass) = 2.10%

All test results produced in accordance with UKAS standards at
an independent UKAS approved laboratory