

# SALTY

## SALTY Premium Matt Lacquer

## Technical Data Sheet

### Type of material

- Environment friendly, water-thinnable opaque wood finish based on the binding agent Decovery®.
- Available in a collection of 10 different colours for interior and exterior use.
- Matt sheen, solvent-free, without wood preservative.
- Consistently ecological choice of raw materials.

### Intended purpose

- As opaque finish on wood, wood-based materials and iron parts, for interior and exterior use.
- The necessary layer thickness and full colour effect are achieved with at least two coats with approximately 0,06 to 0,09 l per m<sup>2</sup>.

### Technical properties

- Tested according to DIN EN 71, part 3, "safe for toys".
- Tested according to DIN 53160, "saliva- and perspiration-proof".
- Values according to EN 13300: Abrasion class 1, Opacity class 1 at a consumption of about 0.08 l/m<sup>2</sup> (corresponds to 12.5 m<sup>2</sup>/l).
- Degree of gloss (approximate values): 15 at 60° measuring angle. The degree of gloss may vary slightly between 10 different colour shades.

### Composition

Water, Decovery®, titanium dioxide, mineral pigments, silicic acid, cellulose, surfactants made of rapeseed oil and castor oil, silicates, liquid ammonia, benzothiazolinone, sodium pyrithione.

### Colour shade

Available in a collection of 10 different colour shades. The colour effect can vary depending on the type of wood (woodgrain) or substrate condition, therefore we recommend a representative test coating before application on large areas. After application, claims based on colour tone variations cannot be accepted.

Due to technical reasons, minor deviations in colour tone can occur between mixtures of the same colour tone tinted on different machine types. For paint mixtures tinted in tinting machines the Technical Guidelines No. 25 of the BFS (Federal Paint and Property Protection Committee) apply.

### Application method

Brushing, rolling (synthetic or mixed-fibre brushes, fine-pore foam rollers, short-pile finishing rollers). AURO offers an assortment of high-grade tools.

The SALTY Premium Matt Lacquer can also be applied by spraying (high pressure, mist-reduced, airmix). Tested with Wagner SF23Plus and pistol Vector Grip. Nozzle type FineFinish TT3, nozzle size 410, gun filter red. Spray pressure 100 bar.

### Drying time at 23°C/ 50% relative humidity

Dust dries after approximately 2 hours, workable after approximately 6 hours, curing time approximately 24 hours.

**Density:** 1.02 - 1.30 g/cm<sup>3</sup>, depending on colour shade.

**Thinner:** Product is ready for use, thinnable with max 5 % water.

**Consumption rate:** 0.06 – 0.09 l/m<sup>2</sup> per coat, corresponds to approx. 70-90 µm wet layer, on smooth, evenly absorbent substrates. Consumption rates depend on substrate, processing method, surface quality. Determine exact consumption on sample.

**Cleaning of tools:** Immediately after use remove product residues from the tools by brushing out and wash with water. Remove stubborn product residues by soaking the tools for longer periods in soap solution and wash thoroughly with water.

**Storage stability:** At 18° C in unopened original container: 24 months.

**Packaging material:** Tinplate.

### Disposal:

Return completely emptied containers for recycling. Only dried product residues can be disposed of as dried paint or with the household waste. Liquid residues: EWC code 080120, designation: paints, lacquers.

### Attention

Product code: BSW10, coating materials, water-based, low in preservatives. Observe standard protective measures, e.g., provide for sufficient skin protection and ventilation during the application. Observe the information on the safe handling of the product, on labelling and hazardous substances contained in the Material Safety Data Sheet (download from [www.saltybyauro.com](http://www.saltybyauro.com)) and on the product label.

**Hazard class:** Does not apply.

**EU VOC value** according to 2004/42/EC II A (dWb): 130 g/l (2010). Product VOC: <= 1 g/l.

# Technical recommendations for application

## SALTY Premium Matt Lacquer

### 1. SUBSTRATE

**1.1 Suitable substrates:** For wood, wood-based materials and iron parts, interior and exterior. Iron parts only after priming with rust protection primer. Can also be used as radiator paint up to 70°C. **Not suited** for floors and for wood with soil contact. Also **not suited** for level surfaces durably exposed to water or surfaces under strong mechanical load (constructive wood protection).

**1.2 General substrate requirements:** The substrate must be clean, firm, free of separating or bleeding substances.

### 2. COATING SYSTEM (UNTREATED WOOD, WOOD-BASED MATERIALS)

**2.1 Substrate preparation:** Round off edges, clean the substrate, roughen (wear a dust mask), remove dust thoroughly. For high-quality surfaces on smooth woods, first wet with sponge, allow to dry, sand finely with the grain, brush out pores, remove all dust and clean. Use only rust-free grinding agents. Wood rich in active substances and resin, tropical woods: wash with alcohol thinner and repeat fine sanding. Remove any substances that come out of the wood such as resin or resin galls; remove damaged wood; seal open wood composites. Wood based materials: seal off the edges watertight.

#### 2.2 Basic treatment:

Test woods rich in ingredients and resins, e.g., larch, for drying problems by applying a test coat!

Wood types rich in active substances have to be primed with a suitable, for example:

- Wood rich in tanning substances (e.g., oak, chestnut, framire etc.) to prevent drying delays
- Wood with bleeding or staining contents, especially before light-coloured or white coatings
- Wood treated with boron salt or boiler pressure impregnated wood to prevent efflorescence.

**2.3 Intermediate treatment:** Fill and level damaged spots with a suited filler. Apply 1 coat of SALTY Premium Matt Lacquer.

**2.4 Final treatment:** Add at least one more coat of SALTY Premium Matt Lacquer. Between coats, fine sanding (220 grit or grinding pad) is recommended, depending on the substrate and surface quality. Be careful not to damage edges and remove all dust thoroughly.

### 3. COATING SYSTEM (UNTREATED IRON PARTS)

**3.1 Substrate preparation:** Iron parts that are not factory-primed: Clean the surface and remove rust down to blank metal with a wire brush or by sanding (60-120 grit). Remove dust. Do not use rust converters.

**3.2 Basic treatment:** Prime with 1 even coat of a rust protection primer. After drying, it is recommended to sand finely (220 grit or grinding pad); do not damage edges; remove dust.

**3.3 Final treatment:** Apply 2 coats of SALTY Premium Matt Lacquer. Repeat coating, if necessary, to achieve the requested colour effect and surface quality.

### 4. COATING SYSTEM (RENOVATION)

#### 4.1 Type of surface: greyed or damaged old coatings (repair)

**4.1.1 Substrate preparation:** Test substrates, old coatings on adhesion and compatibility. Remove non-adhering or unsuitable old coatings, e.g., greyed or heavily weathered old coats, completely, to expose the firm wood structure.

**4.1.2 Subsequent treatment:** New coating sequence as described under item 2.

#### 4.2 Type of surface: intact old coating (maintenance)

**4.2.1 Substrate preparation:** Clean the substrate thoroughly, roughen (wear a dust mask), remove dust.

**4.2.2 Basic treatment:** Does not apply on intact, adhesive surfaces

**4.2.3. Subsequent treatment:** As described under items 2.3 and 2.4.

### 5. CLEANING AND CARE

Either clean surfaces with lukewarm water only or use a suitable paint and stain cleaner. Do not use alkaline solutions (e.g., ammonia or soap solutions), strongly abrasive scouring or cleaning agents, microfibre etc.

#### PLEASE NOTE

- Stir well before use. Slight variations or gradual lowering of gloss degree do not represent a product defect; the same applies for colour shade deviations of different production batches. Check substrate on suitability and compatibility prior to paint application.
- If a thorough surface check cannot be carried out, remove old coatings down to the bare wood or the intact substrate.
- Avoid exposure to direct sunlight, moisture and dirt during processing and drying time.
- Minimum processing temperature: 10°C, max. 30°C, max. 85% rel. humidity; optimal is 20-23 °C at 50-65% rel. air humidity.
- Wood moisture content max. 12% in hardwood 15% in softwood.
- Carry out follow-up coatings promptly, following the recommended coating system.
- Do not expose unfinished coats to weather for longer periods.
- Surfaces must be checked at least once a year and defects be repaired immediately to provide for durable protection. Timely maintenance and repair provide for longer durability.
- Only use sealants and adhesive tapes that are compatible with the product. On windows and doors, the same coating sequence should be applied. Check the sealing of the glass and renew if necessary. Let the coating dry through completely before the windows are closed.
- All coating work must be adapted to the given object and its use. In particular, see Technical Guidelines No. 20, No. 26 of the BFS (Federal Paint and Property Protection Committee).

The Technical Data Sheet gives recommendations and examples of possible use. No liability or other legal responsibility can be derived. Use of the advice does not create any legal relationship. The information provided is based on our present knowledge and does not exempt the user from his personal responsibility. The respective state-of-the-art practices must be observed when implementing coating work and the required preparations. The conditions on site and the product's suitability must be checked appropriately and professionally. With publication of a new edition this technical data sheet is no longer valid. Status: 11.09.2023

SALTY by AURO produced AURO Pflanzenchemie AG • Alte Frankfurter Straße 211a • D-38122 Braunschweig

[productsupport@saltybyauro.com](mailto:productsupport@saltybyauro.com) • [www.saltybyauro.com](http://www.saltybyauro.com)