KODAK 3D Printing Filament

HIPS · Technical Data Sheet

General Features

Chemical Name

High Impact Polystyrene

Benefits

- · High-resolution smooth surfaces
- · Great interlayer adhesion
- · Resistance to shattering

Main Applications

Dissolvable support material for ABS, mate finishing parts, d lemonelo soluble supports, aircraft models.

Filament Characteristics

| Diameter | Ø 1.75mm | Ø 2.85mm |
|------------------|----------|----------|
| Meters per spool | 294.163m | 110.911m |
| Weight per meter | 2.55g | 6.76g |
| Tolerance | ±0.02mm | ±0.03mm |

Material Properties

| | | Typical value | ASTM Method |
|--|-------|----------------|-------------|
| Tensile Strength at Yield, psi | MPa | 2.500 (17) | D 638 |
| Tensile Strength, psi | MPa | 195.000 (1350) | D 638 |
| Tensile Elongation | % | 3.31 | D 638 |
| Izod Impact Strength Notched, ft-lb/in | J/m | 1.7 (95) | D 256 |
| Elongation | % | >50% | - |
| Flow Index | mfr | 80-90 | E 2092 |
| Heat Distortion | °C | 89 | D 648 |
| Density | g/cm3 | 1.06 | D 792 |
| Vicat Softening Temperature | °C | 90 | D 1525 |
| Water Absorption | % | 0.03/0.07 | D 570 |

Recommended printer settings

| Print temperature | 235±5°C |
|-----------------------|----------------------|
| Print bed temperature | 95° First/100° Later |
| Cooling fans | Off |
| Closed environment | Required |
| Adhesive | Required |

Available Colours

| Colour | Pantone Code |
|--------|--------------|
| Black | 6C |
| Blue | 2935 C |
| Red | 485 C |
| White | 11-4001 |

WARNING!

This product can expose you to chemicals including styrene, which is known to the State of California to cause cancer. For more information, go to www.P65Warnings.ca.gov

Disclaimer:

This TDS, based on current knowledge and experience, contains a general summary of hazards and is consistent with the information provided by the supplier. No liability can be assumed for the accuracy and completeness of this information. The information in this TDS applies for this specific material only. It therefore does not apply for its usage in combination with other materials or ways of processing. It is user's responsibility to read and understand this information and incorporate it into individual safety programs, according to all legal and regulatory applicable procedures. Smart International gives no warranty whatsoever, including the warranties of merchantability or of fitness for a particular purpose. Any product purchased is sold on the assumption the user shall determine the quality and suitability of the product. Smart International expressly disclaims any and all liability for incidental, consequential or any other damages arising out of the use or misuse of this product. No information provided shall be deemed to be a recommendation to use any product in conflict with any existing patent rights.

