




ABS-ESD NATURAL KIMYA



The **ABS-ESD NATURAL** is ideal for applications that require protection against electrostatic discharges. This material can be coloured on request.

| IMPACT RESISTANT | EASY TO PRINT
| ELECTROSTATIC DISCHARGE PROTECTION

FILAMENT PROPERTIES


PROPERTIES	TESTS METHODS	UNITS	VALUES
Diameter	INS-6712	mm	1.75 ± 0.1 2.85 ± 0.1
Density	ISO 1183-1	g/cm ³	1.03
Moisture rate	INS-6711	%	<0.5
Melt Flow Index (@220°C – 10 kg)	ISO 1133-1	g/10min	15 - 20
Glass transition temperature Tg	ISO 11357-1	°C	107

PRINT PARAMETERS AND SPECIMENS DIMENSIONS

PRINTING DIRECTION	XY
PRINTING SPEED	40 mm/s
INFILL	100% - rectilinear
INFILL ANGLE	45°/-45°
EXTRUSION TEMPERATURE	260°C
BED TEMPERATURE	100°C


RESULTS

TENSILE TEST




Dim.(mm) : 75x12.5x2
Specimen type ISO 527-5A

BENDING TEST - CHARPY IMPACT



Dim. (mm) : 80x10x4

HARDNESS



Dim.(mm) : 45x45x4

PRINTED SPECIMENS PROPERTIES

	PROPERTIES	TEST METHODS	UNITS	VALUES
ELECTRICAL PROPERTIES	Surface resistivity	ASTM D257	Ohms/m ²	10 ⁷ - 10 ⁹
TENSILE TEST	Tensile modulus	ISO 527-2/5A/50	MPa	1,121
	Strength	ISO 527-2/5A/50	MPa	24.3
	Strain at Strength	ISO 527-2/5A/50	%	3.1
	Stress at break	ISO 527-2/5A/50	MPa	19.8
	Strain at break	ISO 527-2/5A/50	%	6.4
BENDING TEST	Flexural modulus	ISO 178	MPa	856
	Flexural stress at conventional deflection (3,5% strain)*	ISO 178	MPa	27.3
	Flexural strain at flexural strength	ISO 178	%	>5*
CHARPY IMPACT	Charpy impact resistance	ISO 179-1/1eA	kJ/m ²	10.9
HARDNESS	Shore Hardness	ISO 868	Shore D	66.7

*According to ISO 178, end of the test at 5% deformation even if there is no specimen break.