

BRIGHTO EPOXY FLOORING TOPCOAT

General Description	Brighto Epoxy Flooring Topcoat is specially designed for floor chemical resistance coating. It is two component system provides heavy duty floor. It has high chemical resistance and non dusting properties.
Recommend Usage	Industrial areas with heavy loading production plants, workshops, garages, ware houses, etc. It is suitable for concrete surfaces.
Pack Size	Base 4. Liters, 16 Liters Hardener 1 Liter, 4.00 Liters
Colour	Grey
Composition (Nominal)	Pigment: Inert Pigments Binder: Epoxy Resin, Polyamide Resin Solvent: Volatile Solvents DAA, IPA, XYLENE
Finish	Smooth / Sheen
Volume Solids	49 ± 2% (nominal)
Specific Gravity Base	Base or Component A: 1.42 ± 0.05
Specific Gravity Hardener	Hardener or Component B: 0.920 ± 0.05
Mixing Ratio	Base: Hardener (4:1) volume/volume
Pot Life	5 - 6 hours (30°C); 1 - 2 hours (above 40°C);
Induction Time	Use after 15 - 20 minutes (30°C) after mixing
Film Thickness/Coat	Wet: 75 - 100 Micrometers Dry: 36 - 49 Micrometers
Drying Times	Depends on temperature, humidity, air movements and film thickness
Surface Dry Recoat	4 – 5 hours (30°C) 7 – 8 hours (below 15°C) 7 – 8 hours (30°C) 72 hours (below 15°C)
Curing Period	7 Days

Theoretical Coverage	A guide to the theoretical coverage which can be achieved under normal conditions is 10 - 13 m ² /liter /coat.
Application:	Brush, Roller, Scraper and Special Tools
Thinning	10 – 15 % with Brighto Epoxy Thinner (Roller, Brush and Scraper)
Cleaning Up	Clean all equipment with Brighto Epoxy Thinner immediately after use
Surface Preparation and Recommended System	Before application, the surface should be clean, dry (moisture free) and free from oil, grease, dust, wax etc. Rub down the surfaces with the help of abrasive paper/sand stone or mechanical grinder. Clean the surface dust free. Apply 1 – 2 coats of Brighto Epoxy Penetrating Primer Clear. Allow to dry. Slightly rub down the surfaces with the help of abrasive paper where required. Clean the surface till dust free. Apply 2 – 3 coats of Brighto Epoxy Flooring Topcoat. Stir the product thoroughly before use and after mixing properly with component A and component B in recommended ratio. Mix both components (in recommended ratio) as required to current work area and keeping pot life time mentioned above (avoid extra mixing).
Shelf Life	12 Months in original sealed container, proper storage condition (Below 30°C)
Safety, health and Environmental information	Highly inflammable. Keep container tightly closed, up right and out of reach of children. Keep away from the source of ignition e.g. cigarette, matchbox, lighter etc. Protect from extreme of temperature and store in a cool and dry place. Keep away from food, drink and animal feeding stuff. Keep container tightly closed. Wear suitable gloves, mask and safety goggles during application. Do not breathe in vapor and spray mist. May cause Irritating to eyes, skin and respiratory system. Repeated exposure may cause skin dryness. Avoid contact with eyes and skin. In case of contact with eye rinse immediately with plenty of water and seek medical advice. If swallowed, rinse mouth with plenty of water (only if the person is conscious) shows this container or label to a medical practitioner. Its vapor may cause drowsiness and dizziness. In case of fire use foam, dry powder, CO2 fire extinguisher. Never use water. Take precautionary measure against static charges. Use only in well ventilated place. Very toxic to aquatic organisms. May cause long term adverse effects in the aquatic environment. Dispose of paint waste in accordance with the appropriate environment quality regulation.

Any advice recommendations, information, assistance or service provided by Brighto Paints Pvt. Ltd. in relation to goods manufactured or marketed by it or their use or any applications is given in good faith without expressed or implied warranties.