

ESTILPUR 1C



PRODUCT INFORMATION

Polyurethane aliphatic varnish one-component. Solvents free.
 Without yellowing. Applicable indoors and outdoors. High burn resistance.
 Non-flammable product. Water base.

TECHNICAL DATA OF APPLICATION

Product description	Polyurethane aliphatic varnish one-component with water base. It can apply in little or non-existent ventilation areas because it does not contain dissolvent. It does not require mask for organic or chemical vapors, but yes gloves and goggles (only in airless application will be necessary to use comprehensive protection and mask).					
Surface preparation	The supports must be clean, dry, free of powder, fats, oils or contaminants rests that will inhibit adhesion. On absorbent support, primer with two Microestil® Hidrolaca coats, allowed to dry at least 12 hours before apply ESTILPUR 1C.					
Conservation	Approx. 1 year into their original package					
Area of application	On floors and walls both inside and outside for protect the cementitious surfaces and wood surfaces. High hardness surface, resistant to household chemicals and strict mechanical treatment, as well as the action of the permanent water and weather.					
Package	<table border="1"> <tr> <th>Package</th> <th>Container</th> </tr> <tr> <td></td> <td>5 Kg 1 Kg</td> </tr> </table>	Package	Container		5 Kg 1 Kg	
Package	Container					
	5 Kg 1 Kg					
Performance:	150-200gr/m ²					
Use	Although it does not have dregs at rest, it is essential to shake the product in the original container. Apply by microfiber roller or short hair roller, brush or airless. Do not dilute, apply two or three coats more according to desired level protection, it is not necessary to sand between coat and coat if the time is not exceed more 48 hours. The varnish does not acquire all their physical and chemical resistance properties until 7 days.					

ESTILPUR 1 C



Technical Features	Polyurethane aliphatic varnish. Solid content: 40% COV's: 70 g/l Character: nonionic. Finish: satin o matt.
Application conditions	The limits of the temperature for the application must be between +10°C (minimum temperature) and +30°C (maximum temperature). The maximum relative air humidity must be 70 %. The support temperature must be at least 3 ° C above the dew point.
Dry	Traffic 24 hours. Interval between coats: 4 hours Total dried: 7 days.
Cleaning	After using the tools should be cleaned immediately with water.
Cautions	In case of eye contact, visit a doctor. Once hardened is harmless.

NOTE: this technical datasheet serves as all other recommendations and technical information, is to describe the product characteristics, mode of use and applications. The information supplied is based on our technical knowledge obtained in the bibliography, laboratory tests and in practice. The data about consumption and dosage contained in this datasheet is based upon extensive experience so these are susceptible to variations due to the different conditions of work. Real consumption and dosages should be decided on -site through preliminary tests and are the responsibility of the customer. For further advice contact our technical service. Microestil Cement, SL reserves the right to update and change the composition of the products. Other product applications that do not conform to those indicated will not be our responsibility. We give guarantee in case of manufacturing defects quality of our products, excluding any other complaints, only to be our responsibility to return the value of the goods supplied. The present technical datasheet loses your validity with the appearance of a new edition.