

# P541



## PRODUCT INFORMATION

One-component primer water base

### TECHNICAL DATA OF APPLICATION

Product description	Aqueous resin, bridge connecting for cement mortars on porous and non-porous supports, such as mortar, concrete, anhydrite floors, tiles, "terrazo", marble, stoneware... High water resistance.		
Surface preparation	The supports must be firm, clean and without dirt. It must be mechanically removed any contaminant that would prevent from the proper adhesion of the primer to the support. We advise to prepare the support by milling system, blasting or diamond. It is not recommended the preparation by sanding system.		
Conservation	Storage into the original package, closed and avoiding direct sunlight. The product has at least 1 year life. Although it does not have dregs at rest, it is essential to shake the product before their application. Product sensitive to freezing.		
Package	Pot	Pot	Pot
	1kg	5kg	10kg
Consumption	150-250 gr/m <sup>2</sup> .		
Use	Absorbent supports (mortar, concrete, plaster, self-levelings...): Apply the first coat with a brush diluting 1 part of P541 with 2 parts of water. According to the support absorption, apply a second coat with the same dilution, or without diluting you want to put a reinforcement mesh with the same primer. Non-absorbent supports (tile, pottery, "terrazo", marble...): Apply one or two coats with brush without diluting. If you can also put a reinforcement mesh. Do not apply on damp and wet supports.		

# P541



Technical features	Flexible, without residual tack. High water resistance, vapour permeable. Indoor and outdoor. Good alkalin resistance.
Application conditions	Application temperature between 5°C and 35°C. Rying time: 2-4 hours. Clean tools before primer dries.
Dry	2-4 hours.
Cleaning	After using the tools should be cleaned immediately with water.
Cautions	Use resistant protective chemicals gloves. Wear safety glasses with side protection (with frame). Wash hands and / or face before breaks and after to finish work .Avoid contact with the eyes and skin. Use personal protection clothes. Consult the Safety Technical Datasheet.

NOTE: this technical datasheet serves as all other recommendations and technical information, is to describe the product characteristics, mode of use and applications. The information supplied is based on our technical knowledge obtained in the bibliography, laboratory tests and in practice. The data about consumption and dosage contained in this datasheet is based upon extensive experience so these are susceptible to variations due to the different conditions of work. Real consumption and dosages should be decided on -site through preliminary tests and are the responsibility of the customer. For further advice contact our technical service. Microestil Cement, SL reserves the right to update and change the composition of the products. Other product applications that do not conform to those indicated will not be our responsibility. We give guarantee in case of manufacturing defects quality of our products, excluding any other complaints, only to be our responsibility to return the value of the goods supplied. The present technical datasheet loses your validity with the appearance of a new edition.