



	TPU (µm)	Top Coat (µm)	Adhesive (µm)	Liner (µm)	Thickness (µm)	Tensile Strength(ASTM D882)	Elongation at Break (ASTM D882)	Gloss(60°)	Peel Strength (20 min)	Peel Strength (72h)	Aging Test	Stone Chip Resistance (SAE-J400)	Solvent Resistance	Warranty (Years)
Gold Shine	150	9	55	75	214	13	>300	>100	>400 n/m	>400 n/m	NDE	Pass	NDE	7
Black Shine	150	9	55	75	214	13	>300	>85	>400 n/m	>400 n/m	NDE	Pass	NDE	7
Silver Shine	150	9	55	75	214	13	>300	>90	>400 n/m	>400 n/m	NDE	Pass	NDE	7
Champagne Diamond	150	9	40	75	199	15	>250	>90	>400 n/m	>400 n/m	NDE	Pass	NDE	7
Silver Diamond	150	9	40	75	199	15	>250	>90	>400 n/m	>400 n/m	NDE	Pass	NDE	7
Green Diamond	150	9	40	75	199	15	>250	>90	>400 n/m	>400 n/m	NDE	Pass	NDE	7
Blue Diamond	150	9	45	75	204	16	>250	>90	>400 n/m	>400 n/m	NDE	Pass	NDE	7
Pink Diamond	150	9	45	75	204	16	>250	>90	>400 n/m	>400 n/m	NDE	Pass	NDE	7
Purple Chameleon	150	9	47	75	206	15	>250	>90	>400 n/m	>400 n/m	NDE	Pass	NDE	7
Green Chameleon	150	9	47	75	206	15	>250	>90	>400 n/m	>400 n/m	NDE	Pass	NDE	7