



CORTEC
CORPORATION

Environmentally Safe VpCI®/MCI® Technologies

CorrVerter® Rust Converter Primer

DESCRIPTION

CorrVerter® is a fast drying, water-based one-coat system (primer) that converts rusted surfaces to a hydrophobic passive layer and prevents further rusting thru the unique formulation of chelating agents and PVDC resins.

UFI: FM30-30MW-500H-F6AX

PACKAGING & STORAGE

CorrVerter® is available in 1 gallon (3.8 L) and 5 gallon (19 L) pails. Keep product from freezing.

To ensure best product performance, store in original packaging, indoors, and out of direct sunlight at 40-100 °F (4-38 °C).

Shelf life: 1 year



CHARACTERISTICS/TECHNICAL DATA

Volume Solids	34.50% +/- 2%
Gloss (ASTM D532)	15-25
VOCs (ASTM D3960)	0.1 lbs/gal (12 g/L)
Viscosity	7,000-20,000 Centipoise
Pencil Hardness (ASTM D3363)	F
Spreading Rate	553 sq.ft/gal @ 1.0 mils DFT (13.57 sq.m/L @25 µm)
Weight per Gallon	11.59 lbs/gal (1.39 kg/L)
Flash Point	>200 °F (93 °C)
Recommended DFT	3.0-5.0 mils (75-125 µm)
Recommended WFT	5.8-8.7 mils (147-221 µm)
Dry to Touch	2-3 hrs
Dry to Handle	4-6 hrs
Recoat Time	Dry to touch - 72 hrs
Force Dry	15-20 min @ 150 °F (65 °C)
Full Cure	3-7 days
Salt Spray (ASTM B117)	500 hrs
Humidity (ASTM D1748)	250 hrs
Adhesion (ASTM D3359)	5B
Flexibility (ASTM D522)	½" mandrel (1.27 cm)

*All tests performed after a 7 day cure at ambient temperature

CorrVerter® Rust Converter Primer

APPLICATION

Surface Preparation

Substrate should be free of loose rust, grease, oil, dirt, fingerprints, drawing compounds, rust inhibitors (except Cortec® approved), or any other surface contamination that could affect adhesion. Consult Cortec® Technical Service and/or test system adhesion prior to full scale application. It is recommended to remove any loose rust prior to application.

When solvent based topcoats are applied over CorrVerter®, compatibility must be checked. All Cortec® High Performance Coatings can be topcoated over CorrVerter®.

Note: Make sure dew point is more than 5 °F (2 °C) less than air temperature for application. Power agitate to a uniform consistency using a "squirrel cage" type mixer, hand-held drill mixer, or other equivalent method. Can be diluted up to 15% with water. CorrVerter® can be applied by spray, roll, brush, or dip.

Typical Equipment Setups

HVLP / Conventional Spray

- Tip 0.02"-0.11" (0.5-2.8 mm) dependent upon pressures and viscosity
- Air Pressure 45-55 psi
- Fluid Pressure 10 psi
- Fluid hose should be 3/8" (0.95 cm) I.D. with a maximum length of 50 feet (15.2 m). 1/4" (0.64 cm) I.D. fluid hose can be used, but pressures may need to be adjusted. Pot should always have dual regulation and be kept at same elevation as spray gun.

Cleanup

Clean tools/equipment immediately after use with water when paint is still wet. When dry, use butyl cellusolve or MEK. Follow mfg's safety recommendations when using any solvent.

Air Assisted Airless / Airless

- Tip 0.015"-0.035" (0.38-0.89 mm) dependent upon pressures and viscosity
- Pressure 1800-2500 psi
- Hose should be 3/8" (0.95 cm) I.D. minimum, but a 1/4" (0.64 cm) I.D. whip end section may be used for ease of application. A maximum length of 100 feet (30.5 m) is suggested.

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec® Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec® Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec® Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec® Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec® Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec® Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC® CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.

Distributed by:



Valdamark Limited

Unit 13,
30 The Downs
Altrincham, Cheshire, WP14 2PX,
United Kingdom.
valdamark@live.com
Tel: +44 (0) 161 706 0388



4119 White Bear Parkway, St. Paul, MN 55110 USA
Phone (651) 429-1100, Fax (651) 429-1122
Toll Free (800) 4-CORTEC
productinfo@cortecvci.com
https://www.cortecvci.com
https://www.cortecoatings.com

Revised: 02/11/22. Supersedes: 10/06/21. ©Cortec Corporation 2002-2022 of Cortec® Corporation. All Rights Reserved. Copying and/or manipulation of these materials in any form without the written authorization of Cortec® Corporation is strictly prohibited. 2022, ©Cortec® Corp. ISO accreditation applies to Cortec's processes only.

