



EcoLine® 3680

Biobased Open Atmosphere Corrosion Inhibitor

PRODUCT DESCRIPTION

EcoLine 3680 is a temporary coating formulated with USDA (United States Department of Agriculture) certified biobased, renewable, and biodegradable raw materials; which allows use for corrosion protection of equipment where incidental contact with food is possible. EcoLine 3680 leaves a tenacious, dry-to-touch protective coating, wax-like film that can be removed with alkaline cleaners such as Cortec® VpCI-414.

FEATURES

- Formulated with biobased, renewable, and sustainable raw materials
- Excellent indoor and outdoor protection
- Multimetal protection
- USDA certified biobased product
- Biodegradable
- Contains 72% biobased content

TYPICAL APPLICATIONS

- Pipe coating
- Parts storage
- Wire rope
- Steel plate
- Machined parts

TYPICAL PROPERTIES

Appearance	Off white viscous liquid
Coverage	300-330 ft ² /gal @ 3 mils (7-8 m ² /l @ 75 microns)
Dry Film Time	12-24 hours
Film Type	Wax-like
Removal Method	Alkaline cleaner
Carrier	Mineral spirits
VOC	2.9-3.1 lb/gal (347-372 g/l)
Density	7.3-7.8 lb/gal (0.87-0.94 kg/l)
Salt Spray	5-6 mils (125-150 microns), DFT
ASTM B-117	Carbon Steel 1010, 300+ hrs
Humidity	2-3 mils (50-75 microns), DFT
ASTM D-1748	Carbon Steel 1010, 1000+ hrs.

Note: Coating dry time is affected by temperature, air-flow, and humidity.

METALS PROTECTED

- Carbon Steel
- Stainless Steel
- Copper
- Aluminum
- Cast Iron



APPLICATION

EcoLine 3680 may be applied by brushing or spraying. A film thickness of at least 5-6 mils (125-150 microns) is recommended for outdoor use and 2-3mils (50-70 microns) for indoor use.

Surface Preparation:

NACE	SSPC	ARS
3 or 4	6 or 7	High B-2

Product Cleanup:

- Use mineral spirits for cleanup of equipment.
- Alkaline cleaners such as VpCl-414 can be used for clean up of overspray. Cleaners should be heated to 100-200°F (30-48°C) if possible.

RECOMMENDED SPRAY EQUIPMENT

Model	510 Airless/AA Plus
Pump	30:1 President
Tip	0.011-0.015 in (0.028-0.038 cm)
Cap	Standard
Filter	60 Mesh High Pressure
Air Pressure	80 psi
Fluid Hose	3/8" x 10' with 1/4" whip hose for ease of handling
Fluid Pressure (Supply/Gun)	2000/1700 psi (138/117 bar)

The minimum fluid atomization pressure required is 1500 psi (103 bar), which gives 2-4 mils (50-100 microns) WFT/pass.

FOR INDUSTRIAL USE ONLY

KEEP OUT OF REACH OF CHILDREN

KEEP CONTAINER TIGHTLY CLOSED

NOT FOR INTERNAL CONSUMPTION

CONSULT SAFETY DATA SHEET FOR MORE INFORMATION

PACKAGING AND STORAGE

EcoLine 3680 is available in 5 gallon (19 liter) steel pails, 55 gallon (208 liter) metal drums, totes, and bulk. Shelf Life is 24 months @ 75°F (24°C).

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.




4119 White Bear Parkway, St. Paul, MN 55110 USA
Phone (651) 429-1100, Fax (651) 429-1122
Toll Free (800) 4-CORTEC, E-mail info@cortecvci.com
Internet <http://www.cortecvci.com>

Distributed by:



Valdamark Limited
Unit 13,
30 The Downs
Altrincham, Cheshire, WP14 2PX,
United Kingdom.
valdamark@live.com
Tel: +44 (0) 161 706 0388



printed on recycled paper  100% post consumer
Revised: 4/15/14. ©Cortec Corporation 2014. Supersedes: none.
© 2014, ©Cortec Corporation. All Rights Reserved. Copying of these materials in any form without the written authorization of Cortec Corporation is strictly prohibited. ISO accreditation applies to Cortec's processes only.