

ATION  
USA  
FILM  
INHIBITOR-PATENT  
INHIBITOR



## HIGH PERFORMANCE VpCI® PACKAGING

# VpCI®-148 Paper

## Grease Resistant Corrosion Inhibiting Paper



### PRODUCT DESCRIPTION

Cortec® VpCI®-148 is a new and improved grease resistant corrosion inhibiting paper. In addition to its excellent corrosion inhibiting properties, VpCI®-148 also provides resistance to greases, oils, and solvents. Unlike wax or polycoated papers, which contribute to environmental problems, VpCI®-148 contains a biobased coating and is fully recyclable/repulable.

Cortec® VpCI®-148 Paper is made from neutral, natural Kraft paper, and is fluorochemical free, providing an environmentally friendly alternative to traditional grease resistant papers.

### FEATURES

- Provides grease, oil, and solvent resistance
- Oil is not absorbed on the paper but is left captive on the metal surface
- Does not create a hazardous waste like typical waxed, grease-resistant papers
- Protects ferrous and non-ferrous metals
- Comprised of biobased materials
- Free of fluorochemicals, nitrites, phosphates, silicones, chromates, and other heavy metals
- Fully recyclable, repulable
- 3M kit rating of 9
- Protects dry or oiled metals during storage, transit, and overseas shipments from humidity, SO<sub>2</sub>, H<sub>2</sub>S, and galvanic corrosion from dissimilar metals

### TYPICAL APPLICATION

Cortec® VpCI®-148 Paper can be used to protect products that require lubrication (such as bearing and metal parts) in a variety of ways during storage and shipment:

- Single item packaging or interleaving
- Sheet liners or separators between products
- Metalworking: stamping, sheet metal work, springs, bearings, fasteners, tube, pipe, nails, etc.
- Finished products: engines, machinery, equipment, tools, hardware, appliances, instruments, motors, etc.
- Metal forging and die casting: raw and machined forgings and castings

### METALS PROTECTED

- Carbon Steel
- Stainless Steel
- Galvanized Steel
- Cast Iron
- Aluminum Alloys
- Copper
- Brass (≤ 30% Zn)
- Solder

### METHOD OF APPLICATION

Place the printed grease resistant side out and wrap parts in the unprinted side, which contains the corrosion inhibitor, as close to the surface of the product as practical, leaving little to no barrier between the paper and metal surface. Use approximately 1 ft<sup>2</sup> of VpCI® paper for each 3 ft<sup>2</sup> of surface to be protected, and 1 ft<sup>2</sup> of VpCI® paper for every 0.5 ft<sup>3</sup> of void space.

### SIZES

Available in custom sizes and constructions.



## PHYSICAL PROPERTIES

Property	Test Method	Unit	Cortec® VpCI® -148
Basis Weight (Base Stock)	TAPPI T-410	lbs/3000 ft <sup>2</sup> (g/m <sup>2</sup> )	35 (57)
Basis Weight (Finished Product)	TAPPI T-410	lbs/3000 ft <sup>2</sup> (g/m <sup>2</sup> )	44 (72)
Caliper	TAPPI T-411	mil (mm)	3.9 (0.099)
Tear-MD	TAPPI T-414	grams force	48.1
Tear-CD	TAPPI T-414	grams force	46.7
Load @ Break	TAPPI T-494	pounds force	24.5
Elongation @ Break	TAPPI T-494	inches	0.15
% Elongation @ Break	TAPPI T-494	%	2
Tensile Strength @ Break	TAPPI T-494	psi	6134
Grease Resistance	TAPPI T-454	seconds	1800+
Grease Resistance	TAPPI UM- 557	Kit Rating	9

## STANDARD TEST METHODS

NACE TM0208-2008	Vapor Inhibiting Ability
NACE RP0487-2000	Selection of Rust Preventatives
MIL-PRF-3420H	VCI Treated Wrapping Materials, Opaque

**FOR INDUSTRIAL USE ONLY**  
**KEEP OUT OF REACH OF CHILDREN**  
**KEEP CONTAINER TIGHTLY CLOSED**  
**NOT FOR INTERNAL CONSUMPTION**

### LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec® Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec® Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec® Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec® Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec® Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.  
 BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE,

AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec® Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC® CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



4119 White Bear Parkway, St. Paul, MN 55110 USA  
 Phone (651) 429-1100, Fax (651) 429-1122  
 Toll Free (800) 4-CORTEC, E-mail info@cortecvci.com  
<http://www.cortecvci.com>

Printed on recycled paper  100% post consumer

Revised: 06/28/16. Supercedes: 01/07/14. ©Cortec Corporation 2002-2016 of Cortec Corporation.  
 All Rights Reserved. Copying of these materials in any form without the written authorization of Cortec Corporation is strictly prohibited. 2016, ©Cortec Corp. ISO accreditation applies to Cortec's processes only.

Distributed by:



**Valdamark Limited**  
 Unit 13,  
 30 The Downs  
 Altrincham, Cheshire, WP14 2PX,  
 United Kingdom.  
[valdamark@live.com](mailto:valdamark@live.com)  
 Tel: +44 (0) 161 706 0388

