

# VpCI®-388 Water Based Temporary Coating

## DESCRIPTION

VpCI®-388 is a fast drying, water-based temporary coating that provides protection in harsh, outdoor, sheltered applications. Provides multi-metal protection. Can be matched to some custom colors. Provides a non-tacky film.

## PACKAGING & STORAGE

VpCI®-388 is available in 5 gallon (19 liter) pails, 55 gallon (208 liter) metal drums, liquid totes, and bulk. Keep product from freezing.

Product shelf life is 1 year.



## CHARACTERISTICS/TECHNICAL DATA

Volume Solids	26.70%
Gloss (ASTM D532)	NA
VOCs (ASTM D3960)	0.2 lbs/gal (24 g/l)
Viscosity	5,000-15,000 Centipoise
Pencil Hardness (ASTM D3363)	NA
Spreading Rate	428 sq.ft/gal @ 1.0 mills DFT (10.5 sq.m/l @ 25 µm)
Weight per Gallon	8.57 lbs/gal (1.02 kg/l)
Flash Point	>200°F (93°C)
Recommended DFT	2.0-3.0 mils (50-75 µm)
Recommended WFT	7.5-11.25 mils (187.5-281.5 µm)
Dry to Touch	20-30 min
Dry to Handle	45-60 min
Recoat Time	NA
Force Dry	15-20 min @ 150°F (65°C)
Full Cure	3-7 days
Salt Spray (ASTM B117)	200 hrs
Humidity (ASTM D1748)	200 hrs
Adhesion (ASTM D3359)	5B
Flexibility (ASTM D522)	1/2" mandrel (1.27cm)

\*All tests performed after a 7 day cure at ambient temperature

# VpCI®-388 Water Based Temporary Coating

## APPLICATION

### Surface Preparation

Substrate should be free of grease, oil, dirt, fingerprints, drawing compounds, rust inhibitors, or any other surface contamination that could affect adhesion. For structural steel applications, Cortec® recommends a minimum of a NACE #3/SSPC-SP6 commercial blast clean. Consult Cortec® and/or test system adhesion prior to full scale application.

**Note: Make sure dew point is more than 5°F (2°C) less than air temperature for application. Power agitate to a uniform consistency using a "squirrel cage" type mixer, hand-held drill mixer, or other equivalent method. VpCI®-388 can be applied by spray, roll, brush, or dip.**

### Typical Equipment Setups

#### HVLP / Conventional Spray

- Tip .009"-.021" \*dependent upon pressures and viscosity
- Air Pressure 45-55 psi
- Fluid Pressure 10 psi
- Fluid hose should be 3/8" (0.95 cm) I.D. with a maximum length of 50 feet (15.2 m). Pot should always have dual regulation and be kept at same elevation as spray gun.

#### Air Assisted Airless / Airless

- Tip .015"-.035" \*dependent upon pressures and viscosity
- Pressure 1800-2500 psi
- Hose should be 3/8" (0.95 cm) I.D. minimum, but a 1/4" (0.64 cm) I.D. whip end section may be used for ease of application. A maximum length of 100 feet (30.5 m) is suggested.

### Cleanup

Clean tools/equipment immediately after use with water when coating is still wet. When dry, use Butyl Cellusolve or MEK. Follow mfg's safety recommendations when using any solvent.

#### LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec® Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec® Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec® Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec® Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec® Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

**BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH.** No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec® Corporation.

**THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC® CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.**



4119 White Bear Parkway, St. Paul, MN 55110 USA  
Phone (651) 429-1100, Fax (651) 429-1122  
Toll Free (800) 4-CORTEC  
info@cortecvci.com  
http://www.cortecvci.com  
http://www.cortecoatings.com

Distributed by:



**Valdamark Limited**  
Unit 13,  
30 The Downs  
Altrincham, Cheshire, WP14 2PX,  
United Kingdom.  
valdamark@live.com  
Tel: +44 (0) 161 706 0388

