



M-528/ 528 L



TYPICAL PROPERTIES

M-528

Appearance	Clear yellowish to amber liquid
pH	8-9 (1% in water)
Density	8.5-8.7 lb/gal (1.02-1.03 kg/l)
Non-volatile (weight)	50-60% (M-528) 295°F (146°C)

M-528L

Appearance	Clear yellowish to amber liquid
pH	7.5-8.5 (1% in water)
Density	8.6-8.8 lb/gal (1.03-1.06 kg/l)
Non-volatile (weight)	60-70% (M-528L)

PRODUCT DESCRIPTION

M-528/528L are the additives for hydraulic fluids used in subsea production control systems and other water based process fluids.

They provide corrosion protection for steel, copper, brass, aluminum, bronze, galvanized steel, and other ferrous and non-ferrous metals and their alloys. M-528/528L prevent corrosion in both phases: contact and vapor.

M-528L contains an additional lubricant package.

FEATURES

- Stable in aqueous systems at pH of 6 or above
- Soluble in water, glycols and alcohols; insoluble in hydrocarbon-based solvents; dispersible in oils
- Non-phenolic
- Seawater compatible
- Thermostable
- Was evaluated with good results in Ethylene Glycol/water blend according to IP287 with and without seawater addition
- Falex test data show that antiwear properties of Ethylene glycol/water based fluid containing M-528L are excellent
- Biodegradable
- Non-hazardous, environmentally friendly
- M-528 is in compliance with HOCNF (Harmonized Offshore Chemical Notification Format) environmental requirements

APPLICATIONS

- Hydraulic fluids used in subsea production control systems
- Synthetic coolants and cutting fluids
- Industrial cooling towers
- Water based lubricants
- Aerosol formulations
- Alkaline metal cleaners
- Radiator fluid additive
- Water based drilling muds



TEST RESULTS

Test Performed		Results
IP287	a. Liquid corrosion test on neat fluid	No Corrosion
	b. with 10% of seawater	No Corrosion
	c. with 2.5% of seawater	No Corrosion
IP125: Vapor phase corrosion test		Pass
10% by volume seawater contamination		Clear Fluid
Stability at	Room temperature	Clear Stable
	70°C	Clear Stable
	-20°C	Clear Stable

*All tests were performed in the the solution

Ethylene Glycol/water=40:50 with added 10% of M-528 or M-528L

Falex Lubricant Testing Ethylene Glycol/water 40:50 with 10% of M-528L

Load (lb) at (min)	Torque values (lb.in)
100(1)	6.3
200(1)	10.7
300(1)	13.3
400(1)	17.8
500(1)	21.3
500(30)	18.2
Number of tests	6
% Weight loss on pin	0.058%

FOR INDUSTRIAL USE ONLY
KEEP OUT OF REACH OF CHILDREN
KEEP CONTAINER TIGHTLY CLOSED
NOT FOR INTERNAL CONSUMPTION
CONSULT SAFETY DATA SHEET FOR MORE INFORMATION

STANDARD TEST METHODS

OECD Method 301D	Biodegradable
ASTM D-4172	4-Ball Wear Test
ASTM D-130	Copper Strip Corrosion
ASTM D-665	Rust Preventing Characteristics
ASTM D-974	Acid/Base Number by Titration
ASTM D-1748	Humidity Testing
ASTM D-2196	Brookfield Viscometer

PACKAGING AND STORAGE

M-528/528L are packaged in 5 gallon (19 liter) pails, 55 gallon (208 liter) drums, liquid totes, and bulk.

These products should be stored sealed in a heated warehouse to avoid freezing. M-528/528L have a shelf life of 24 months.

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec® Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec® Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec® Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec® Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec® Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.
 BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE,

AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec® Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC® CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



4119 White Bear Parkway, St. Paul, MN 55110 USA
 Phone (651) 429-1100, Fax (651) 429-1122
 Toll Free (800) 4-CORTEC, E-mail info@cortecvci.com
<http://www.cortecvci.com>

Printed on recycled paper  100% post consumer

Revised: 01/24/17. Supersedes: 09/24/13. ©Cortec Corporation 2002-2016 of Cortec Corporation. All Rights Reserved. Copying of these materials in any form without the written authorization of Cortec Corporation is strictly prohibited. 2016, ©Cortec Corp. ISO accreditation applies to Cortec's processes only.

Distributed by:



Valdamark Limited

Unit 13,
 30 The Downs
 Altrincham, Cheshire, WP14 2PX,
 United Kingdom.
valdamark@live.com
 Tel: +44 (0) 161 706 0388

