

Technical Data Sheet

Ultracur3D® RG 3280

Rigid | HDT 280 | Ceramic-filled

General Properties	Norm	Typical values
Appearance	-	White
Viscosity, 30 °C	Cone/Plate Rheometer ¹	230 mPas
Viscosity, 50 °C	Cone/Plate Rheometer ¹	93 mPas
Density (printed part)	ASTM D792	1.73 g/cm ³
Density (liquid resin)	ASTM D4052-18a	1.65 g/cm ³

Tensile Properties	Norm (5 mm/min)	Typical values (UV post-cured)	Typical values (UV + thermal*)
E Modulus	ASTM D638	10000 MPa	10300 MPa
Ultimate Tensile Strength	ASTM D638	76 MPa	70 MPa
Elongation at Break	ASTM D638	1 %	0.7 %

Flexural Properties	Norm	Typical values (UV post-cured)
Flexural Modulus	ASTM D790	8780 MPa
Flexural Strength	ASTM D790	73 MPa

Impact Properties	Norm	Typical values (UV post-cured)
Notched Izod (Machined), 23 °C	ASTM D256	2.36 J/m
Unnotched Izod, 23 °C	ASTM D256	4.67 J/m
Charpy notched, 23 °C	ISO 179-1	0.98 kJ/m ²

Thermal Properties	Norm	Typical values (UV post-cured)	Typical values (UV + thermal*)
HDT at 0.45 MPa	ASTM D648	>280 °C	>280 °C
HDT at 1.82 MPa	ASTM D648	132 °C	162 °C

Hardness	Norm	Typical values (UV post-cured)
Shore D	ASTM D2240	96

Other	Norm	Typical values
Water Absorption, Short Term (24 hours)	ASTM D570	0.29 %

1) Determined with TA-Instrument DHR rheometer, cone/plate, diameter 60 mm, shear rate 100 s⁻¹

* regular UV post-curing and additional thermal post-cure of 3h at 150°C, see User Guideline for more details.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. The safety data given in this publication is for information purposes only and does not constitute a legally binding MSDS. The relevant MSDS can be obtained upon request from your supplier or you may contact BASF 3D Printing Solutions GmbH directly at sales@basf-3dps.com. Version 1.0