



Product Data

Description

RS007 LV Polyaspartic is a solvent based two component 66% solids polyaspartic aliphatic urethane clear coating. RS007 has excellent chemical resistance, hardness, abrasion resistance, UV stability and has an excellent clear gardner color. RS007 is its exceptionally quick tack free time of around 1-2 hours for foot traffic.

Coverage Per Gallon Kit:

200 - 800 square feet per gallon at 2 - 8 mils wet

Packaging

2 gallon kits (net approximately)

10 gallon kits (net approximately)

Color

Clear

Gloss

>70 at 60 degrees

Shelf Life

Six Months unopened when properly stored

Features

Recommended for areas where a thin or medium build clear coat is desired over a broadcast system and installation downtime is very limited. This product is suitable as a thin or medium build coating and topcoat. USDA approved.

Where to Use

- garage floors
- auto service centers
- warehouses
- laboratories
- aircraft hangers
- cafeterias
- Food and Beverage Facilities

Primer

Recommend a suitable primer and testing to determine suitability.

Topcoat

Not recommended

See full application instructions

Physical Data

Color	Clear, can be pigmented with appropriate colorant
Mix Ratio	One to one by volume
DFT	2 - 8 mils
Finish	Gloss >70 at 60 degrees

Cure Schedule (70°F)

Pot Life	< 1 hours
Tack Free	1-2 hours
Recoat or Topcoat	2-3 hours
Light Foot Traffic	1-4 hours
Full Cure	24-48 hours

Application Temperature

50-90 degrees F with relative humidity below 85%

Chemical Resistance

Chemical	Rating
Xylene	C
MEK	A
1,1,1 trichloroethane	B
Methanol	B
Ethyl Alcohol	B
Skydrol	C
50% sodium hydroxide	E
10% sulfuric acid	C
10% HCl (aq)	C
5% acetic acid	C

Rating key: NR - not recommended, B - 2 hour term splash spill, C - 8 hour term splash spill, D - 72 hour immersion, E - long term immersion. NOTE: additional chemical resistance information is available through Plexicoat.

Typical Properties after 5 days

Abrasion Resistance

Taber abraser CS-17 calibrase wheel with 1000 gram total load and 500 cycles = 21 mg loss

Compressive Strength

12,000 psi @ ASTM D695

Tensile Strength

3,900 psi @ ASTM D638

Ultimate Elongation

2.4%

Hardness

Shore D=80

Viscosity

<200 Centipose

Limitations

Due to the quick cure rate and dry time, it is suggested that the user obtain a sample and thoroughly evaluate the product before using.

Color stability may be affected by environmental conditions like high humidity/chemical exposure. Exposure to some types of lighting such as sodium vapor lights may cause discolorations.

Test Data based on neat resin.

Clarity of color may vary from batch to batch.

Substrate temperature must be 5°F above dew point.

Too thick of an application may result in surface imperfections, bubble generation or product failure.

Always apply a test patch to determine product suitability and adhesion performance for your proposed application method and procedures.

All new concrete must be cured for at least 30 days prior to application.

Do not expose this product to water until fully cured.

Physical properties are typical values and not specifications.

See reverse side for application instructions.

For professional use only.

LIMITED WARRANTY NOTICE Every reasonable effort is made to apply Resins Plus exacting standards both in the manufacture of our products and in the information which we issue concerning these products and their use. We warrant our products to be of good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, Resins Plus MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS, and Resins Plus shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the Resins Plus Technical Manager. This information and all further technical advice are based on Resins Plus's present knowledge and experience. However, Resins Plus assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, Resins Plus disclaims all CONDITIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. Resins Plus SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. Resins Plus reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.

Resins Plus LLC

Bonita Springs, FL 34135 • (352) 995-7587

www.resinsplus.com • info@resinsplus.com



RS007 LV POLYASPARTIC APPLICATION INSTRUCTIONS

PRODUCT STORAGE: Store product at normal room temperature before using. Storage should be between 60 and 90 degree F.

SURFACE PREPARATION: The most suitable surface preparation would be a brush blast (shot blast) to remove all laitance and provide a suitable profile. All dirt, foreign contaminants, oil and laitance must be removed to assure a trouble free bond to the substrate. A test should be made to determine that the concrete is dry; this can be done by placing a 4'X4' plastic sheet on the substrate and taping down the edges. If after 24 hours, the substrate is still dry below the plastic sheet, then the substrate is dry enough to start coating. The plastic sheet testing is also a good method to determine if any hydrostatic pressure problems exist that may later cause disbonding.

PRODUCT MIXING: This product has a mix ratio of one to one by volume. Standard packages are in pre-measured kits and should be mixed as supplied in the kit. After the two parts are combined, mix well with slow speed mixing equipment such as a jiffy mixer until the material is thoroughly mixed and streak free. After mixing, transfer the mixed material to another pail (the transfer pail) and again remix. The material in the transfer pail is now ready to be applied on the properly prepared surface.

PRIMING: A suitable primer should be used before applying this product. However, whether a primer is used or not, it is advisable to apply a test patch prior to using this product to determine if the adhesion characteristics are suitable for the service environment.

PRODUCT APPLICATION: The mixed material can be applied by brush or roller. Maintain temperatures and relative humidity within the recommended ranges during the application and curing process. This product is only intended for use as a thin build topcoat. Improper mixing may result in product failure. It should be pointed out that relative humidity can have a dramatic influence on the curing characteristics. The product will dry quicker and have less working time when the relative humidity is higher while a lower relative humidity will lengthen the dry time and working time.

RECOAT OR TOPCOATING: This material can be applied in multiple coats. If you opt to recoat this product, you must first be sure that the coating has tacked off before recoating. Always remember that colder temperatures will require more cure time for the product before recoating can commence.

CLEANUP: Use xylol

FLOOR CLEANING: Caution! Some cleaners may affect the color of the floor installed. Test each cleaner in a small area, utilizing your cleaning technique. If no ill effects are noted, you can continue to clean with the product and process tested.

RESTRICTIONS: Restrict the use of the floor to light traffic and non-harsh chemicals until the coating is fully cured (see technical data under full cure). It is best to let the floor remain dry for the full cure cycle. Dependent on actual complete system application, surface may be slippery, especially when wet or contaminated; keep surface clean and dry.