



RS3425

WB Epoxy

Product Data

Description RS3425 is a two component water based epoxy coating that exhibits excellent characteristics that rival solvent based products. RS3425 has good chemical resistance, abrasion resistance, and substrate penetration. This product has a tack free time of about 3 hours and can support traffic in as little as 6-12 hours.

Solids by Weight:

43% (+/- 2%)

Solids by Volume:

40% (+/- 2%)

Yield**Coverage Per Gallon Kit:**

229 to 320 square feet @ 5-6 mils wet thickness

Packaging

2 gallon and 5 gallon kits (volume approx.)

Color

Off white, light gray, medium gray, tile red, beige, and amber clear. NOTE: The clear (gardner 11) is not water clear and is not suitable for topcoating over previously color coated floors. The clear is suitable as a primer or concrete sealer only.

Mix Ratio

6.95# part A (.80 gallons, approximate) to
1.75# part B (.20 gallons, approximate).

Finish Characteristics

Gloss (>60 @ 60 degrees @ glossmeter)

Shelf Life

1 year in unopened containers

Where to Use

Recommended for priming or coating concrete, wood or masonry. This product can withstand exposure to many common solvents and chemicals.

Primer None required

Topcoat Optional – Many products are suitable as topcoats including multiple coats of this product. For added chemical resistance, color stability, or UV stability, topcoat with a suitable aliphatic urethane.

See full application instructions

Physical Data

Color	Clear
Mix Ratio	6.95# part A (.80 gallons, approximate) to 1.75# part B (.20 gallons, approximate).
DFT	2-3.5 mils
Finish	Gloss (>60 @ 60 degrees @ glossmeter)
VOC	Less than 95 g/l

Cure Schedule (70°F)

Pot Life	2 hours
Tack Free	2-4 hours
Recoat or Topcoat	4-6 hours
Light Foot Traffic	6-12 hours
Full Cure	2-5 days

Application Temperature 55-90 degrees F with relative humidity below 85%

Chemical Resistance

	Rating
acetic acid 5%	B
xylene	B
mek	A
gasoline	B
10% sodium hydroxide	C
10% sulfuric	B
10% hydrochloric acid	B
20% nitric acid	A

Rating key: NR - not recommended, B - 2 hour term splash spill, C - 8 hour term splash spill, D - 72 hour immersion, E - long term immersion. NOTE: additional chemical resistance information is available through Resins Plus.

Typical Properties after 5 days

Abrasion Resistance Taber abrasor CS-17 calibrase wheel with 1000 gram total load and 500 cycles = 45 mg loss

Impact Resistance
Gardner Impact, direct = 50 in. lb. (passed)

Flexural Strength
8,200 psi @ ASTM D790

Flexibility
No cracks on a 1/8" mandrel

Adhesion
425 psi @ elcometer (concrete failure, no delamination)

Viscosity
400-900 cps (typical)

Limitations

Color or gloss may be affected by humidity, low temperatures, chemical exposure, or sodium vapor lighting. Product will yellow in the presence of UV light. For best results use a 1/4 or 3/8" nap roller. Slab on grade requires moisture barrier. Substrate temperature must be 5°F above dew point. All new concrete must be cured for at least 30 days. Product color will vary from batch to batch. Use only product from same batch for an entire job. Improper mixing or too thick of an application may result in product failure. Physical properties listed on this technical data sheet are typical values and not specifications. See reverse side for application instructions. See reverse side for limitations of liability & warranty.

For professional use only.

LIMITED WARRANTY NOTICE Every reasonable effort is made to apply Resins Plus exacting standards both in the manufacture of our products and in the information which we issue concerning these products and their use. We warrant our products to be of good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, Resins Plus MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS, and Resins Plus shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the Resins Plus Technical Manager. This information and all further technical advice are based on Resin Plus's present knowledge and experience. However, Resins Plus assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, Resins Plus disclaims all CONDITIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. Resins Plus SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. Resins Plus reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.

Resins Plus LLC

Bonita Springs, FL 34135 · (352) 995-7587

www.resinsplus.com · info@resinsplus.com

RS3425 Fast Cure Water Based Epoxy Primer APPLICATION INSTRUCTIONS

PRODUCT STORAGE: Store product in an area so as to bring the material to normal room temperature before using. Continuous storage should be between 60 and 90 degree F. Keep from freezing.

SURFACE PREPARATION: Surface preparation will vary according to the type of complete system to be applied. For a one or two coat thin build system (3-10 mils dry) we recommend either mechanical scarification or acid etching until a suitable profile is achieved. For a complete system build higher than 10 mils dry, we recommend a fine brush blast (shot blast). All dirt, oil, dust, foreign contaminants and laitance must be removed to assure a trouble free bond to the substrate. A test should be made to determine that the concrete has an appropriate vapor barrier. This can be done by placing a 4' X 4' plastic sheet on the substrate and taping down the edges. If after 24 hours, the substrate is still dry below the plastic sheet, then the substrate does not show signs of eventual hydrostatic pressure problems that may later cause disbonding. However, this product can be applied to a damp floor as long as there are no standing puddles.

PRODUCT MIXING: This product comes pre-packaged by weight. Kits should be mixed in their entirety. If partial kits are to be used, refer to the front of this technical data for proper weight mix ratios. After the two parts are combined, mix well with slow speed mixing equipment such as a jiffy mixer until the material is thoroughly mixed and streak free. This product is an emulsion product and should be mixed well before using.

PRODUCT APPLICATION: The mixed material can be applied by brush or roller. Maintain temperatures within the recommended ranges during the application and curing process. Apply material with relative humidity within the parameters shown on the technical data. When the end of the pot life has been reached, you will find that the material becomes hard to apply and will actually tend to roll back up onto the roller. Do not try to continue application when the coating has reached this step. Applications made at different times with differing environmental conditions, may show slight variations in gloss.

RECOAT OR TOPCOATING: If you opt to recoat or topcoat this product, you must first be sure that all of the solvents and water have evaporated from the coating during the curing process. The information on the front side are reliable guidelines to follow. However, it is best to test the coating before recoating and topcoating. This can be done by pressing on the coating with your thumb to verify that no fingerprint impression is left. If no impression is created, then the recoat or topcoat can be started. Always remember that colder temperatures will require more cure time for the product before recoating or topcoating can commence. Before recoating or topcoating, check the coating to insure no epoxy blushes were developed (a whitish, greasy film or deglossing). If a blush is present, it must be removed prior to topcoating or recoating. A standard type detergent cleaner can be used to remove any blush. Many epoxy overlays and coatings as well as urethanes are compatible for use as a topcoat for this product as well as multiple coats of this product.

CLEANUP: Use PM solvent

FLOOR CLEANING: Caution! Some cleaners may affect the color of the floor installed. Test each cleaner in a small area, utilizing your cleaning technique. If no ill effects are noted, you can continue to clean with the product and process tested.

RESTRICTIONS: Restrict the use of the floor to light traffic and non-harsh chemicals until the coating is fully cured (see technical data under full cure). It is best to let the floor remain dry for the full cure cycle. Dependent on actual complete system application, surface may be slippery, especially when wet or contaminated; keep surface clean and dry.