



## TEST REPORT

No.2019041013906EN

Date: Apr 12,2019

Page 2 of 3

### Tests Conducted (As Requested By The Applicant):

Dimensional Stability To Washing(ISO 5077:2007/ISO 3759:2011/ISO 6330:2012; Procedure No.: 4N; Using Horizontal Axis, Front-Loading Type Machine: Machine Wash At 40°C With 2 Kg Total Dry Mass (Type III (100%Polyester)+Specimen), And ECE(A) Detergent + Sodium Perborate + TAED, Followed By Tumble Dry Low)

		<u>Requirement</u>
Warp	-2.5%	± 5%
Weft	-1.5%	± 5%

**Remark:** (+) Means Extension (-) Means Shrinkage

Appearance After Washing(ISO 6330:2012; Procedure No.: 4N; Using Horizontal Axis, Front-Loading Type Machine: Machine Wash At 40°C With 2 Kg Total Dry Mass (Type III (100%Polyester)+Specimen), And ECE(A) Detergent + Sodium Perborate + TAED, Followed By Tumble Dry Low)

		<u>Requirement</u>
Pilling And Fuzzing Hair	4-5	Min.3
Any Observed Defects	Satisfactory	Satisfactory

Colour Fastness To Washing(ISO 105-C06:2010 A2S,Single Test, 30 Minutes Mechanical Wash At 40°C In 0.4% ECE Reference Detergent Solution,1g/L Sodium Perborate With 10 Steel Balls)

		<u>Requirement</u>
Change In Shade	4-5	Min.4
Staining On Multi-Fiber Stripe		Min.3
-Acetate	4-5	
-Cotton	4-5	
-Nylon	4-5	
-Polyester	4-5	
-Acrylic	4-5	
-Wool	4-5	

**Remark:** Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.

Colour Fastness To Rubbing(ISO 105-X12:2016)

		<u>Requirement</u>
Dry	4-5	Min.3-4
Wet	4-5	Min.2-3

**Remark:** Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.

The Results Shown In This Report Refer Only To Sample(s) Tested Unless Otherwise Stated. (除非有其他说明, 测试结果只对来样负责。)  
This Test Report Cannot Be Reproduced, Except In Full. (本报告只能全部复制, 不得部分复制。)

**Zhejiang Max Testing Technical Services Co., Ltd. 浙江迈克思检测技术服务有限公司**

5F,9B, No.8 Haining Avenue, Haining Economic Development Zone, Zhejiang Province, China 浙江省海宁经济开发区海宁大道8号9幢5楼  
Tel.: +86(0) 573-87006955 Web: www.maxzj.com E-mail: CS@maxzj.com

## TEST REPORT

No.2019041013906EN

Date: Apr 12,2019

Page 3 of 3

### Colour Fastness To Drycleaning(ISO 105-D01:2010)

Change In Shade	4-5
Staining On Multi-Fiber Stripe	
-Acetate	4-5
-Cotton	4-5
-Nylon	4-5
-Polyester	4-5
-Acrylic	4-5
-Wool	4-5

### Requirement

Min.4  
/

**Remark:** Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.

### *Suggested Care:*



### **Photo Appendix:**



\*\*\*End of Report\*\*\*

The Results Shown In This Report Refer Only To Sample(s) Tested Unless Otherwise Stated. (除非有其他说明, 测试结果只对来样负责。)  
This Test Report Cannot Be Reproduced, Except In Full. (本报告只能全部复制, 不得部分复制。)

**Zhejiang Max Testing Technical Services Co., Ltd. 浙江迈克思检测技术服务有限公司**

5F,9B, No.8 Haining Avenue, Haining Economic Development Zone, Zhejiang Province, China 浙江省海宁经济开发区海宁大道8号9幢5楼  
Tel.: +86(0) 573-87006955 Web: www.maxzj.com E-mail: CS@maxzj.com