



Test Report

SAY NO TO CORRUPTION

Sr. No. 89

Test Report No. PPD/ATR - 82

Date: 17 -01-2020

Name & Address of Client: Xinuan International Engg. Co. (pvt) Ltd.

Description of the Sample

Item: Rubber Waterstop

Mark if any: nil

Date of Receipt: 07-01-2020

Make: Not Known

Condition Found on Receipt: Normal

Sample Plan/Procedure Used: As provided by the client Date of Sampling: Not known

Environmental Condition: Temp: 20°C


Humidity: 49 %

Measurements & Results:


S.No.	TESTS	Methods Used	RESULTS
1.	Hardness (Shore-A)	ASTM D 2240	58 ± 1
2.	Tensile Strength	ASTM D 412	19.3 MPa
3.	Elongation at break	ASTM D 412	1000 %
4.	Tear Strength	ASTM D 1004	50 kN/m


For tensile properties : GL: 25 mm, Speed : 500 mm / mn

Tested by


Hydayal Ahmed

Checked by


17-01-2020



Head of Centre/Division

CHAIRMAN

Department of Polymer &
Petrochemical Engineering
NED University of Engg. &
Technology Karachi-75720