

MONDERCANGE

Composition	41% REC.COT - WV 6% - PL 39% - PC 14%		Width Cm.	140
Weight gr./square	735	± 5%	Warp Cm.	35
Weight gr./linear	1030	± 5%	Weft Cm.	14



TEST

METHOD

RESULTS

MARTINDALE ABRASION 12KPA	UNI EN ISO 12947-2	50.000
PILLING	ISO 12945-2	50.000 rubs
COL.FASTNESS TO ARTIFICIAL LIGHT	UNI EN ISO 105-B02	5/6
SEAM SLIPPAGE WEFT/WARP	UNI EN ISO 13936-2	4 mm
SEAM SLIPPAGE WARP/WEFT	UNI EN ISO 13936-2	6 mm
COL.FASTNESS TO DRY RUBBING	UNI EN ISO 105-X12	4/5
COL.FASTNESS TO WET RUBBING	UNI EN ISO 105-X12	3
COL.FASTNESS TO DRY WASH CHANGE	UNI EN ISO 105-D01	4
COL.FASTNESS TO DRY WASH STAIN	UNI EN ISO 105-D01	4
COMBUSTION RESISTANCE: CIGARETTE TEST	BS 5852 source 0	PASS
COMBUSTION RESISTANCE: CIGARETTE TEST	CAL.TB117:2013	PASS

Other info: RECYCLED COTON