

Codice Articolo **361712** **PERSEIDE**Settore **01 Arredamento**Tariffa Doganale **54079300**Composizione **WO 35% PC 35% PL 23%
CO 7%**Altezza Cm. **140**Peso al Mq. in Gr. **414** $\pm 5\%$ Fili Cm. **34**Peso al Mtl. in Gr. **587** $\pm 5\%$ Trame Cm. **16**

Test	Norma	Valore
ABRASIONE MARTINDALE 12KPA	UNI EN ISO 12947-2	40000
PILLING	ISO 12945-2	3/4 5000 rubs
SOLIDITA' COL.LUCE ARTIFICIALE	UNI EN ISO 105-B02	5/6
SCOR.CUCITURE TRAMA/ORDITO	UNI EN ISO 13936-1	>200
SCOR.CUCITURE ORDITO/TRAMA	UNI EN ISO 13936-1	>200
SOL.SFREGAMENTO SECCO	UNI EN ISO 105-X12	4/5
SOL.SFREGAMENTO UMIDO	UNI EN ISO 105-X12	3
STAB.DIM.LAVAGGIO A SECCO TRAMA	UNI EN ISO 5077	-1%
STAB.DIM.LAVAGGIO A SECCO ORDITO	UNI EN ISO 5077	-1%
RES.TRAZIONE TRASVERSALE	UNI EN ISO 13934-1	437
RES.TRAZIONE LONGITUDINALE	UNI EN ISO 13934-1	911
SOL.COL.LAVAGGIO A SECCO DEGRADO	UNI EN ISO 105-D01	4
SOL.COL.LAVAGGIO A SECCO SCARICO	UNI EN ISO 105-D01	4
RESISTENZA COMBUSTIONE: CIGARETTE TEST	BS 5852 source 0	PASS
RESISTENZA COMBUSTIONE: CIGARETTE TEST	CAL.TB117:2013	PASS
RESISTENZA COMBUSTIONE: CIGARETTE TEST	EN 1021-1	PASS

STANDARD
10020CX00047
CENTROCOT