

Solid carbide end mills

End mills (4-fluted)




Catalog no. 64525



P	M	K	N	S	H
●	○	●			

Application
recomm. p. 570

- centre cutting
- universal application



d1 h10 mm	d2 h6 mm	l1 mm	l2 mm	l3 mm	c mm x 45°	Z	Code no.
2.000	6.000	57.000	7.000	9.900	0.025	4	2.000
3.000	6.000	57.000	8.000	12.400	0.050	4	3.000
4.000	6.000	57.000	11.000	15.900	0.050	4	4.000
5.000	6.000	57.000	13.000	19.400	0.050	4	5.000
6.000	6.000	57.000	13.000	21.000	0.050	4	6.000
7.000	8.000	63.000	16.000	23.900	0.100	4	7.000
8.000	8.000	63.000	19.000	27.000	0.100	4	8.000
10.000	10.000	72.000	22.000	32.000	0.100	4	10.000
12.000	12.000	83.000	26.000	38.000	0.100	4	12.000
14.000	14.000	83.000	26.000	38.000	0.150	4	14.000
16.000	16.000	92.000	32.000	44.000	0.150	4	16.000
18.000	18.000	92.000	32.000	44.000	0.150	4	18.000
20.000	20.000	104.000	38.000	54.000	0.150	4	20.000

Application recommendations for Carbide Slot Drills and End Mills

		Feed column																Feed f (mm/tooth)
Code-letter	H	I	J	K	L	M	N	O	P	Q	R	S	T	U	V	W		
tool-Ø mm	2.00	0.001	0.001	0.001	0.002	0.002	0.004	0.005	0.006	0.007	0.008	0.010	0.012	0.014	0.016	0.018	0.020	
	3.00	0.002	0.002	0.003	0.003	0.004	0.007	0.010	0.010	0.010	0.015	0.016	0.013	0.019	0.022	0.024	0.030	
	5.00	0.005	0.006	0.007	0.009	0.010	0.014	0.020	0.020	0.022	0.025	0.026	0.026	0.028	0.030	0.032	0.038	
	6.00	0.006	0.008	0.009	0.011	0.013	0.017	0.024	0.025	0.027	0.031	0.029	0.033	0.039	0.036	0.041	0.047	
	8.00	0.010	0.012	0.014	0.016	0.019	0.024	0.032	0.032	0.035	0.042	0.042	0.047	0.053	0.052	0.058	0.064	
	10.00	0.013	0.015	0.018	0.021	0.025	0.030	0.038	0.039	0.044	0.050	0.053	0.059	0.065	0.066	0.073	0.080	
	12.00	0.010	0.018	0.022	0.026	0.030	0.036	0.046	0.048	0.052	0.059	0.063	0.072	0.079	0.085	0.090	0.100	
	16.00	0.020	0.023	0.027	0.032	0.038	0.045	0.054	0.058	0.063	0.071	0.079	0.088	0.095	0.100	0.110	0.120	
	20.00	0.023	0.028	0.033	0.038	0.045	0.057	0.066	0.073	0.080	0.090	0.097	0.100	0.110	0.120	0.130	0.140	
	25.00	0.030	0.035	0.040	0.045	0.055	0.065	0.075	0.100	0.120	0.130	0.140	0.150	0.165	0.170	0.180	0.190	

a_e = Width of cut
a_p = Cutting depth



a_e = 0.1 x D

Feed rate codes in bold are the preferred choice for the respective material group.

Oblique plunging and slot milling

For oblique plunging the feed rate (v_f = mm/min) should be reduced as illustrated.

In addition, chip evacuation is required for drilling depths in excess of 1 x D. This also applies to the transition to radial machining.

slot milling

a_p = cut. depth 0.5 x D = f_z 100%

a_p = cut. depth 1.0 x D = f_z 75%

Drilling

For drilling the feed rate (v_f = mm/min) should be reduced as illustrated.

In addition, chip evacuation is required for larger drilling depths in excess of 0.5 x D.



Lubricants:

- cutting oil, highly activated ■
- soluble oil (emulsion) ■
- air only

Material group	Materials examples, new designations (old designation in brackets) Figures in bold = material no. to DIN EN	Tensile strength MPa (N/mm ²)	Hardness	Coolant
General purpose steels	1.0035 S185(St33), 1.0486 P275N(StE285), 1.0345 P235GH(H1), 1.0425 P265GH(H2) 1.0050 E295 (St50-2), 1.0070 E360 (St70-2), 1.8937 P500NH (WStE500)	≤500 >500-850		■
Free-cutting steels	1.0718 11SMnPb30 (9SMnPb28), 1.0736 11SMn37 (9SMn36) 1.0727 46S20 (45S20), 1.0728 (60S20), 1.0757 46SPb20 (45SPb20)	≤850 850-1000		■
Unalloyed tempering steels	1.0402 C22, 1.1178 C30E (Ck30) 1.0503 C45, 1.1191 C45E (Ck45) 1.0601 C60, 1.1221 C60E (Ck60)	≤ 700 700-850 850-1000		■
Alloyed tempering steels	1.5131 50MnSi4, 1.7003 38Cr2, 1.7030 28Cr4 1.5710 36NiCr6, 1.7035 41Cr4, 1.7225 42CrMo4	850-≤1000 1000-1200		■
Unalloyed case hardened steels	1.0301 (C10), 1.1121 C10E (Ck10)	≤750		■
Alloyed case hardened steels	1.7043 38Cr4 1.5752 15NiCr13 (15NiCr13), 1.7131 16MnCr5, 1.7264 20CrMo5	850-≤1000 1000-1200		■ ■
Nitriding steels	1.8504 34CrAl6 1.8519 31CrMoV9, 1.8550 34CrAlNi7	≥850-≤1000 >1000-1200		■ ■
Tool steels	1.1750 C75W, 1.2067 102Cr6, 1.2307 29CrMoV9 1.2080 X210Cr12, 1.2083 X42Cr13, 1.2419 105WCr6, 1.2767 X45NiCrMo4	≤850 >850-1000		■ ■
High speed steels	1.3243 S 6-5-2-5, 1.3343 S 6-5-2, 1.3344 S 6-5-3	≥650-1000		■
Spring steels	1.5026 55Si7, 1.7176 55Cr3, 1.8159 51CrV4 (51CrV4)		≤330 HB	■ ■
Hardened steels	-		≤40-48 HRC >48-60 HRC	■ ■
Stainless steels, sulphured austenitic martensitic	1.4005 X12CrS13, 1.4104 X14CrMoS17, 1.4105 X6CrMoS17, 1.4305 X8CrNiS18-9 1.4301 X5CrNi18-10 (V2A), 1.4541 X6CrNiTi18-10, 1.4571 X6CrNiMoTi 17-12-2 (V4A) 1.4057 X20CrNi17.2 (X17CrNi16-2), 1.4122 X39CrMo17-1, 1.4521 X2CrMoTi18-2	≤850 ≤850 ≤850		■ ■ ■
Cast iron	0.6010 EN-GJL-100(GG10), 0.6020 EN-GJL-200(GG20) 0.6025 EN-GJL-250(GG25), 0.6035 EN-GJL-350(GG35)	850-≤1000 1000-1200		■ □
Spheroidal graphite iron and malleable cast iron	0.7050 EN-GJS-500-7(GGG50), 0.8035 EN-GJMW-350-4(GTW35) 0.7070 EN-GJS-700-2(GGG70), 0.8170 EN-GJMB-700-2(GTS70)		≤240 HB <300 HB	■ ■
Chilled cast iron	-		≤350 HB	■
New Cast iron GGV	EN-GJV250 (GGV25), EN-GJV350 (GGV35) EN-GJV400 (GGV40), EN-GJV500 (GGV50), SiMo6			■ □
New Cast iron ADI	EN-GJS-800-8 (ADI800), EN-GJS-1000-5 (ADI1000) EN-GJS-1200-2 (ADI1200), EN-GJS-1400-1 (ADI1400)	800-1000 1200-1400		■ □
Special alloys	Nimonic, Inconel, Monel, Hastelloy	≤1200		■
Ti and Ti-alloys	3.7024 Ti99.5, 3.7114 TiAl5Sn2.5, 3.7124 TiCu2 3.7154 TiAl6Zr5, 3.7165 TiAl6V4, 3.7184 TiAl4Mo4Sn2.5, - TiAl8Mo1V1	≤850 >850-1200		■ ■
Aluminium and Al-alloys	3.0255 Al99.5, 3.2315 AlMgSi1, 3.3515 AlMg1	≤400		■
Al wrought alloys	3.0615 AlMgSiPb, 3.1325 AlCuMg1, 3.3245 AlMg3Si, 3.4365 AlZnMgCu1.5	≤450		■
Al cast alloys ≤ 10 % Si	3.2131 G-AlSi5Cu1, 3.2153 G-AlSi7Cu3, 3.2573 G-AlSi9	≤600		■
> 10 % Si	3.2581 G-AlSi12, 3.2583 G-AlSi12Cu, - G-AlSi12CuNiMg	≤600		■
Magnesium alloys	3.5200 MgMn2, 3.5812.05 G-MgAl8Zn1, 3.5612.05 G-MgAl6Zn1	≤450		□
Copper, low alloyed	2.0070 SE-Cu, 2.1020 CuSn6, 2.1096 G-CuSn5ZnPb	≤400		■ ■
Brass, short-chipping	2.0380 CuZn39Pb2, 2.0401 CuZn39Pb3, 2.0410 CuZn43Pb2	≤600		■ ■
long-chipping	2.0250 CuZn20, 2.0280 CuZn33, 2.0332 CuZn37Pb0.5	≤600		■ ■
Bronze, short-chipping	2.1090 CuSn7ZnPb, 2.1170 CuPb5Sn5, 2.1176 CuPb10Sn	≤600		■ ■
	2.0790 CuNi18Zn19Pb	>600-850		■ ■
Bronze, long-chipping	2.0916 CuAl5, 2.0960 CuAl9Mn, 2.1050 CuSn10 2.0980 CuAl11Ni, 2.1247 CuBe2	≤850 >850-1000		■ ■
Duroplastics	Epoxy resin, Resopal, Pertinax, Moltopren			- □
Thermoplastics	Plexiglas, Hostalen, Novodur, Makralon			- ■ □
Kevlar	Kevlar			- □
Glass/carbon-concentr. plastics	GFK/CFK			- □

Fine finishing

Catalog no.	74525	54526	64525 54524	74424	54444	74204	74202	74206	74479	
Tool mat.	Solid carbide		Solid carbide		Solid carbide		Solid carbide		Solid carbide	
Std.	6527 L		6527 L		Stock std.		6527 K 6527 L		Stock std.	
Type	N		N		N		W		W	
Page	609	613	610/608	602	611	584	585	586	587	



V _c m/min	Feed col.												
116	S	193	S	76	N	127	O						
106	R	176	S	70	M	116	N						
116	R	193	S	76	M	127	N						
86	Q	143	R	60	L	99	M						
116	R	193	S	76	M	127	N						
106	R	176	S	66	M	110	N						
86	Q	143	R	57	L	94	M						
103	Q	171	R	66	L	110	M						
86	P	143	Q	57	L	94	L						
129	R	215	S	73	M	121	N						
103	R	171	S	66	M	110	N						
76	Q	127	R	50	L	83	M						
116	R	193	S	76	M	127	N						
106	P	176	Q	66	L	110	L						
103	R	171	S	66	M	110	N						
86	P	143	Q	57	L	94	L						
66	Q	110	R	43	L	72	M						
66	P	110	Q										
39	N	55	O										
66	Q	110	R										
57	P	94	Q										
53	Q	88	R										
139	R	231	S	99	M	165	N						
139	Q	231	R	90	L	149	M						
126	R	209	S	83	M	138	N						
106	Q	176	R	70	L	116	M						
73	O	121	P										
40	P	66	Q										
66	P	110	Q	43	L	72	L						
53	O	88	P	33	K	55	L						
561	T	935	T	330	P	550	Q	418	U	330	P	523	U
528	S	880	T	396	O	660	P	506	T	396	O	633	T
274	S	457	S	165	N	275	O	203	T	165	N	253	T
225	S	374	T	132	O	220	P	165	T	132	P	207	T
317	T	528	T	198	P	330	Q	241	U	198	U	302	U
146	S	242	T	99	O	165	P	115	T	99	P	143	T
132	S	220	S	80	N	132	O	102	T	80	N	127	T
106	S	176	S	66	N	110	O	95	T	66	N	119	T
132	S	220	S	80	N	132	O	102	T	80	N	127	T
99	R	165	S					90	S			112	S
99	R	165	S					90	S			112	S
86	Q	143	R					76	S			95	S
146	Q	242	R					115	S			143	S
132	Q	220	R					102	S			127	S