



INSPECTION CERTIFICATE According to EN 10204 3.1

CUSTOMER : SPECIALISED WELDING PRODUCTS-U.K.										MTR NO. / ISSUE DATE		EXP-867/29.03.2023			
										PART NO.		7162			
										BATCH NO.		M-13563			
										GRADE		ER 307Si/(G 18 8 Mn)			
										SUPPLY CONDITION		STAINLESS STEEL MIG WELDING WIRE			
INVOICE NO./P.O. NO. : EXP/22-23/939 DT-29.03.2023/42306 DT-28.02.2023										SURFACE FINISH		BRIGHT DRAWN, BRIGHT FINISH			
CHEMICAL COMPOSITION OF WIRE :-															
SR. NO.	DIAMETER (mm)	NUMBER OF SPOOLS	WEIGHT (KGS)	HEAT NO SPECIFIED	%C	%Mn	%Si	%S	%P	%Cr	%Ni	%Cu	%Mo	%N2	
ELEMENTS %					MIN	-	5.00	-	-	-	17.00	7.00	-	-	
					MAX	0.20	8.00	1.20	0.030	0.030	20.00	10.00	0.50	0.50	
1	1.00 (BS300/15KGS)	36	540.00	CH-18825	0.050	6.14	0.88	0.006	0.029	18.08	8.20	0.16	0.140	0.0560	
MECHANICAL PROPERTIES OF WIRE :-															
SL. NO.	SAMPLE DIAMETER	TENSILE STRENGTH	0.2% PROOF STRESS	ELONGATION %	REDUCTION OF AREA %	CHARPY IMPACT VALUE (Joules) Temp. AT (RT)	FERRITE NO (FN) (WRC-1992)	INCLUSION RATING							
-	(mm)	(N/mm ²)	(N/mm ²)	Lo=100	-	-	-	A	A	A	A	A			
-	(mm)	(N/mm ²)	(N/mm ²)	Lo=100	-	-	-	THICK THIN	THICK THIN	THICK THIN	THICK THIN	THICK THIN			
1	1.00	1697	-	-	-	-	5	-	-	-	-	-			
SPECIFICATION :-															
TENSILE STRENGTH			AS PER DIN EN ISO 14343-A												
DIAMETER TOLERANCE			AS PER ISO 544												
% ELONGATION			STANDARD												
MATERIAL SPECIFICATION			MATERIAL CONFORMS TO DIN EN ISO 14343-A												
MATERIAL IS FREE FROM MERCURY CONTAMINATION , FREE FROM WELD AND WELD REPAIRS .															
RADIOACTIVITY TEST : WE CONFIRM THE MATERIAL HAS BEEN TESTED AND FOUND TO BE FREE FROM RADIOACTIVE CONTAMINATION.															
WE HEREBY CERTIFY THAT THE MATERIAL DESCRIBED ABOVE HAS BEEN TESTED AND COMPLIES WITH THE TERMS OF ORDER / CONTRACT.															

Specialised Welding Products Ltd

Unit 1, Withins Point, Withins Road, Haydock Industrial Centre, Haydock, WA11 9UD, UK T: 01942 719930 E: sales@swp.uk.net

www.specialisedwelding.co.uk