



INSPECTION CERTIFICATE According to EN 10204 3.1

CUSTOMER : SPECIALISED WELDING PRODUCTS-U.K.					MTR NO. / ISSUE DATE					EXP-340/31.08.2023				
					PART NO.					7190				
INVOICE NO./P.O. NO. : EXP/23-24/388 DT-31.08.2023/43065 DT-25.07.2023					BATCH NO.					M-14645				
					GRADE					ER 308LSi/(G 19 9L Si)				
					SUPPLY CONDITION					STAINLESS STEEL MIG WELDING WIRE				
					SURFACE FINISH					BRIGHT DRAWN, BRIGHT FINISH				
CHEMICAL COMPOSITION OF WIRE :-														
SR. NO.	DIAMETER (mm)	NUMBER OF SPOOLS	WEIGHT (KGS)	HEAT NO SPECIFIED	%C	%Mn	%Si	%S	%P	%Cr	%Ni	%Cu	%Mo	%N2
ELEMENTS %				MIN	-	1.00	0.65	-	-	19.00	9.00	-	-	-
				MAX	0.030	2.50	1.20	0.020	0.030	21.00	11.00	0.50	0.50	-
1	0.80 (BS300/15KGS)	36	540.00	20137	0.024	1.74	0.80	0.004	0.023	19.56	9.18	0.19	0.099	0.0805
MECHANICAL PROPERTIES OF ALL WELD METAL :-														
SL. NO.	TENSILE STRENGTH	0.2% PROOF STRESS	ELONGATION %	REDUCTION OF AREA %	CHARPY IMPACT VALUE (Joules) Temp. AT (RT)	FERRITE NO (FN) (WRC-1992)	INCLUSION RATING							
							A	A	A	A	A			
-	(N/mm ²)	(N/mm ²)	Lo=100	-	-	-	THICK THIN	THICK THIN	THICK THIN	THICK THIN	THICK THIN	THICK THIN	THICK THIN	THICK THIN
1	642	486	36	72	106	9	-	-	-	-	-	-	-	-
SPECIFICATION :-														
TENSILE STRENGTH			AS PER DIN EN ISO 14343-A											
DIAMETER TOLERANCE			AS PER ISO 544											
% ELONGATION			STANDARD											
MATERIAL SPECIFICATION			MATERIAL CONFORMS TO DIN EN ISO 14343-A											
COUNTRY OF ORIGIN			INDIA											
MATERIAL IS FREE FROM MERCURY CONTAMINATION , FREE FROM WELD AND WELD REPAIRS .														
RADIOACTIVITY TEST : WE CONFIRM THE MATERIAL HAS BEEN TESTED AND FOUND TO BE FREE FROM RADIOACTIVE CONTAMINATION.														
WE HEREBY CERTIFY THAT THE MATERIAL DESCRIBED ABOVE HAS BEEN TESTED AND COMPLIES WITH THE TERMS OF ORDER / CONTRACT.														

Specialised Welding Products Ltd

Unit 1, Withins Point, Withins Road, Haydock Industrial Centre, Haydock, WA11 9UD, UK T: 01942 719930 E: sales@swp.uk.net

www.specialisedwelding.co.uk