



## INSPECTION CERTIFICATE According to EN 10204 3.1

CUSTOMER : SPECIALISED WELDING PRODUCTS-U.K.					MTR NO. / ISSUE DATE		EXP-411/10.11.2022							
					PART NO.		7225							
INVOICE NO./P.O. NO. : EXP/22-23/528 DT-10.11.2022/41482 DT-05.09.2022					BATCH NO.		T-13521							
					GRADE		ER 316L/( W 19 12 3 L)							
					SUPPLY CONDITION		STAINLESS STEEL TIG WELDING WIRE							
					SURFACE FINISH		BRIGHT DRAWN, BRIGHT FINISH							
<b>CHEMICAL COMPOSITION OF WIRE :-</b>														
SR. NO.	DIAMETER (mm)	NUMBER OF PKTS	WEIGHT (KGS)	HEAT NO SPECIFIED	%C	%Mn	%Si	%S	%P	%Cr	%Ni	%Cu	%Mo	%N2
<b>ELEMENTS %</b>				<b>MIN</b>	-	<b>1.00</b>	-	-	-	<b>18.00</b>	<b>11.00</b>	-	<b>2.00</b>	-
				<b>MAX</b>	<b>0.030</b>	<b>2.50</b>	<b>0.65</b>	<b>0.030</b>	<b>0.030</b>	<b>20.00</b>	<b>14.00</b>	<b>0.75</b>	<b>3.00</b>	-
1	2.40 X 1000	40	800.00	<b>CH-17784</b>	0.020	1.90	0.41	0.006	0.029	18.61	11.17	0.44	2.060	0.0750
<b>MECHANICAL PROPERTIES OF ALL WELD METAL :-</b>														
SL. NO.	TENSILE STRENGTH	0.2% PROOF STRESS	ELONGATION %	REDUCTION OF AREA %	CHARPY IMPACT VALUE (Joules) Temp. AT (RT)	FERRITE NO (FN) (WRC-1992)	INCLUSION RATING							
							A	A	A	A	A			
-	(N/mm <sup>2</sup> )	(N/mm <sup>2</sup> )	Lo=100	-	-	-	THICK THIN	THICK THIN	THICK THIN	THICK THIN	THICK THIN	THICK THIN	THICK THIN	THICK THIN
1	624	465	38	72	96	7	-	-	-	-	-	-	-	-
<b>SPECIFICATION :-</b>														
TENSILE STRENGTH DIAMETER TOLERANCE % ELONGATION MATERIAL SPECIFICATION			AS PER DIN EN ISO 14343-A AS PER ISO 544 STANDARD MATERIAL CONFORMS TO DIN EN ISO 14343-A											
MATERIAL IS FREE FROM MERCURY CONTAMINATION , FREE FROM WELD AND WELD REPAIRS . <b>RADIOACTIVITY TEST</b> : WE CONFIRM THE MATERIAL HAS BEEN TESTED AND FOUND TO BE FREE FROM RADIOACTIVE CONTAMINATION.														
<b>WE HEREBY CERTIFY THAT THE MATERIAL DESCRIBED ABOVE HAS BEEN TESTED AND COMPLIES WITH THE TERMS OF ORDER / CONTRACT.</b>														