



INSPECTION CERTIFICATION

According to EN 10204 3.1

Client	SWP	Heat No.	8127	Date of Delivery	Dec., 15, 2023
Products	Super 6 SG2	Test No.	838127	Date of Production	Dec., 2023
Order no.	43632	Size	1.2mm(7309)	Date of Test	Dec., 8, 2023

All-weld-metal/Chemical analysis(%)-CO2/MIXED GAS

C	Si	Mn	P	S	Cr	Ni	Mo	V	Al	Ti+Zr	Cu
0.08	0.89	1.57	0.013	0.011	0.006	0.004	0.004	0.003	0.002	0.03	0.22

Welding conditions

Current type	DC+	Arc voltage(V)	22-26	Inter pass temp.	150
Current(A)	220-260	Shielding Gas	EN ISO 14175-C1,M20,M21		

All-weld-metal mechanical properties

Tensile test

Test no.	Heat treatment	Tensile strength(MPa)	Yield Strength(MPa)	Elongation(%)
838127	-	548	457	28

Impact test

Test no.	Notch type	Test temperature	Shielding Gas	Impact value(J)					Average
				1	2	3	4	5	
838127	V	-40	M21	97	96	95	94	94	95.20
838127	V	-40	C1	82	82	83	84	83	82.80

Radiography

Bending test(Butt Weld)

Hydrogen Test

II	OK	2.78
----	----	------



Standard no.: AWS A5.18 ER70S-6

EN ISO 14341-A-G 42 4C1/M21 3Si1

DIN 8559 SG2

Approvals: TÜV SÜD

CPR Certificate no.:0036-CPR-S 128.2020.001

We hereby certify that the product described above "complies with the term of the order" and conforms with the related international standards"

0036

14

DOP Ref.:Super 6 SG2 2017-001

EN13479:2017

Inspecting Department : QC Department

Inspector : **Jeremy Packer**

Specialised welding Products Ltd

Unit 1 , Withins Road, Haydock Industrial Estate, Haydock, WA11 9UD

www.specialisedwelding.co.uk