



## INSPECTION CERTIFICATION

According to EN 10204 3.1

Client	SWP	Heat No.	8818	Date of Delivery	March 20, 2023
Products	<b>Super 6 SG2</b>	Test No.	838818	Date of Production	March, 2023
Order no.	42084	Size	1.0mm(7313)	Date of Test	March 16, 2023

### All-weld-metal/Chemical analysis(%)-CO2/MIXED GAS

C	Si	Mn	P	S	Cr	Ni	Mo	V	Al	Ti+Zr	Cu
0.09	0.88	1.56	0.013	0.012	0.007	0.005	0.004	0.003	0.002	0.03	0.22

### Welding conditions

Current type	DC+	Arc voltage(V)	22-26	Interpass temp.	150
Current(A)	220-260	Shielding Gas	EN ISO 14175-C1,M20,M21		

### All-weld-metal mechanical properties

Tensile test									
Test no.	Heat treatment	Tensile strength(MPa)		Yield Strength(MPa)		Elongation(%)			
838818	-	547		458		28			
Impact test									
Test no.	Notch type	Test temperature	Shielding Gas	Impact value(J)					Average
				1	2	3	4	5	
838818	V	-40	M21	93	88	87	88	89	89.00
838818	V	-40	C1	83	84	82	86	85	84.00
Radiography			Bending test(Butt Weld)			Hydrogen Test			
II			OK			2.78			



Standard no.: AWS A5.18 ER70S-6  
EN ISO 14341-A-G 42 4C1/M21 3Si1  
DIN 8559 SG2

Approvals: TÜV SÜD

CPR Certificate no.:0036-CPR-S 128.2020.001

We hereby certify that the product described above "complies with the term of the order" and conforms with the related international standards"

0036

14

DOP Ref.: Super 6 SG2 2020-001

EN13479:2017

Inspecting Department : QC Department

Inspector : **Jeremy Packer**

Specialised welding Products Ltd

Unit 1 , Withins Road, Haydock Industrial Estate, Haydock, WA11 9UD

[www.specialisedwelding.co.uk](http://www.specialisedwelding.co.uk)