



## INSPECTION CERTIFICATE

According to EN 10204 3.1

Client	SWP	Heat No.	4290	Date of Delivery	July 12, 2023
Products	<b>SUPER 6SG3</b>	Test No.	5434290	Date of Production	June., 2023
Order no.	42618	Size	1.2mm(7322)	Date of Test	July 10, 2023

### All-weld-metal/Chemical analysis(%)-CO2/MIXED GAS

C	Si	Mn	P	S	Cr	Ni	Mo	V	Al	Ti+Zr	Cu
0.08	0.96	1.79	0.013	0.012	0.006	0.005	0.003	0.002	0.002	0.04	0.22

### Welding conditions

Current type	DC+	Arc voltage(V)	22-26	Interpass temp.	150
Current(A)	220-260	Shielding Gas	EN ISO 14175-C1,M20,M21		

### All-weld-metal mechanical properties

#### Tensile test

Test no.	Heat treatment	Tensile strength(MPa)	Yield Strength(MPa)	Elongation(%)
5434290	-	548	467	27

#### Impact test

Test no.	Notch type	Test temperature	Shielding Gas	Impact value(J)					Average
				1	2	3	4	5	
5434290	V	-40	M21	88	91	92	87	88	89.20
5434290	V	-40	C1	82	82	83	85	83	83.00

Radiography	Bending test(Butt Weld)	Hydrogen Test
II	OK	2.75



Standard no.: AWS A5.18 ER70S-6

EN ISO 14341-A-G 42 4C1 4Si1

EN ISO 14341-A-G 46 4M21 4Si1

DIN 8559 SG3

0036

14

DOP Ref.: Super SG3 2014-001

EN13479:2017

Approvals: TÜV SÜD

CPR Certificate no.: 0036-CPR-S 128.2020.001

We hereby certify that the product described above "complies with the term of the order" and conforms with the related international standards"

Inspecting Department : QC Department

Inspector : **Jeremy Packer**

Specialised welding Products Ltd

Unit 1 , Withins Road, Haydock Industrial Estate, Haydock, WA11 9UD

[www.specialisedwelding.co.uk](http://www.specialisedwelding.co.uk)