



**INSPECTION CERTIFICATE** According to EN 10204 3.1

No.7401 4500 7397

Designation	E6013	Specification	Φ 2.5 X 350mm	Batch No.	122308 1	Date	2023-8-18	Quantity	7.6t
<b>CHEMICAL COMPOSITIONS OF DEPOSITED METAL</b>									
COMPOSITIONS		C	Mn	Si	S	P			
REQUIREMENTS		≤0.12	0.30-0.60	≤0.30	≤0.035	≤0.040			
RESULT		0.79	0.33	0.16	0.024	0.023			
Mechanical Properties of Deposited Metal					ButtWeld				
Tensile Test				Impact Test					
	Y.P(MPa)	T.S(MPa)		Temp.	Value(J)			NDT	
	≥330	≥420	≥17	0°C	≥27			I	
	405	450	21	0°C	59	60	61	60	I
(Surface Appearance Quality: EXCELLENT)									
APPROVED BY	GRADE		Quality Management System Audit		ISO9001-2015		(ml/100g)		
CE TUV									
GB/T5117-2012 (Fitted as GB/T5117-2012 Covered electrodes for manual metal arc welding of non-alloy and fine grain steel E4313 AWS A5.1 E6013									

**Specialised Welding Products Ltd**

Unit 1, Withins Point, Withins Road, Haydock Industrial Centre, Haydock, WA11 9UD, UK T: 01942 719930 E: sales@swp.uk.net

[www.specialisedwelding.co.uk](http://www.specialisedwelding.co.uk)