



INSPECTION CERTIFICATE According to EN 10204 3.1

No.7402 4501

Designation	E6013	Specification	Φ 3.2 X 350mm	Batch No.	132310 1	Date	2023.10.18	Quantity	9.7t	
CHEMICAL COMPOSITIONS OF DEPOSITED METAL										
COMPOSITIONS		C	Mn	Si	S	P	其它			
REQUIREMENTS		≤0.12	0.30-0.60	≤0.30	≤0.035	≤0.040				
RESULT		0.078	0.35	0.17	0.025	0.024				
Mechanical Properties of Deposited Metal							ButtWeld			
Tensile Test				Impact Test				NDT		
	Y.P(MPa)	T.S(MPa)	%	Temp.	Value(J)					
	≥330	≥420	≥17	0°C	≥27			I		
	410	445	22	0°C	61	62	60	61	I	
(Surface Appearance Quality: EXCELLENT)										
APPROVED BY	GRADE		Quality Management System Audit		ISO9001-2015		(ml/100g)			
CE TUV										
GB/T5117- (Fitted as GB/T5117-2012 Covered electrodes for manual metal arc welding of non-alloy and fine grain steel E4313 AWS A5.1 E6013										