



# Superon Schweisstechnik India Ltd

Plot no. 552, Pace City-II, Sector 37, Gurgaon,  
Haryana-122001, India

An ISO 9001 , ISO 14001 &  
BS OHSAS 18001 Certified Company

## TEST CERTIFICATE AS PER EN 10204 TYPE:3.1

CUSTOMER : SWP-U.K

P.O./P.I. NO	41777/04.11.2022
INVOICE NO./DATE	EXP/22-23/680/29.12.2022
QTY.(Kgs.)	140.00

Brand/Grade: SUPER OPTIMAL 6010

Report No: SUP 2022/5212

Size ( mm ) : 3.20X350

Date of issue: 29.12.2022

Standard-No./  
Classifications: AWS A5.1: E6010

PART No.7406

Batch No/Heat No: GP 16384

Date of Mfg: 20.12.2022

### All Weld Metal Chemical Analysis (%)

Element	C	Si	Mn	S	P	Cr	Ni	Mo	Cu	Nb	V	N
Spec.	0.20 MAX.	1.00 MAX.	1.20 MAX.	N.S.	N.S.	0.20 MAX.	0.30 MAX.	0.30 MAX.	-	-	0.08 MAX.	-
Result	0.12	0.19	0.68	0.010	0.018	0.015	0.11	0.003	-	-	0.003	-

### Mechanical Properties of All Weld Metal

	Yield Strength (N/mm <sup>2</sup> )	Tensile Strength (N/mm <sup>2</sup> )	Elongation (%)	Charpy Impact Avg. value(Joules) Temp. At -30 (°C)	Hardness (As welded)	Ferrite(FN) as per WRC-1992
Spec:	330 Min.	430 Min.	22 Min.	27 Min.	-	-
Result	415	516	26.20	54,66,60,58,58 Avg.=58.67	-	-

Diffusible Hydrogen:- (ml/100gm of weld metal)	--	Coating Moisture (%):-	--
Radiography:-	Satisfactory	Fillet weld Test:-	Satisfactory
Bend Test:-	--	PWHT:-	--

TEST CONDUCTED AS PER : AWS/SFA-A5.1 : E6010

We certify that the statement in this test report are correct and that the test welds were prepared welded and tested in Accordance with the requirement conforming to ASME BPVC.II.C Latest Edition 2021, in all respects.



Manager Quality Assurance

Corporate Office : Plot No. 552, Sector – 37, Pace City – II, Gurgaon, Haryana-122001, India

Tel. : +91-124-4940900. E-mail : [export@superoncorp.com](mailto:export@superoncorp.com), Website: [www.superoncorp.com](http://www.superoncorp.com)