



Part No. 1818

Description:

Application:

特性 Characteristic	单位 Unit	数据 Data						测试标准 Method
织纹 Weave	Unit	8HS SATIN 缎纹						
用纱 Yarn	tex	经纱		WARP	纬纱		WEFT	
		EC9 136 1x2			EC9 136 1x2			
重量 Weight	g/m ²	600						ASTM-D3776-2009
厚度 Thickness	mm	0.7mm						ASTM-D1777-1996
密度 Thread Count	per cm	经纱	WARP	18	纬纱	WEFT	13	ASTM-D3775-2008
涂层类型 Coating								
涂层重量 Coating Weight	g/m ²							ASTM-D3776-2009
产品总重 Total Weight	g/m ²	600						ASTM-D3776-2009
产品总厚 Total Thickness	mm	0.7						ASTM-D1777-1996
抗张强度 Tensile Strength	N/2.5cm	经纱	WARP	2750	纬纱	WEFT	1650	ASTM-D5034-2001
耐温度 Service Temperature	°C	1100						
获得认证 Certification		欧洲 BSEN 476 PART 7						
		欧盟 CE						
		美国 FM 4950						
		GB 8624-2012 不燃等级 A1 级						
		FTP Code Part1 船用不燃材料						

m 0.914

m 45.7