TECHNICAL DATA SHEET

FLEXIBLE PU

• Product Code: FPU

PRODUCT INFORMATION

Dae Ha Flexible PU is a high quality, super stretchable HTV.

- Outstanding flexibility with excellent rebound properties.
- Environmentally friendly and PVC free.
- Semi-matt finish.
- No curling for easier work processes.
- Easy to cut and weed.
- Suitable for fine detail.
- Wide range of available colors.

MATERIAL SPECIFICATION

- * Composition: PU
- * Adhesive carrier
- * Thickness: 90 ± 15μm
- * Standard roll size: 500mm x 50M

EXIBLE P

CUTTING & TRANSFER CONDITIONS Plotter Machine: GCC Jaguar IV / Mimaki CJV150 75

Я	Cut Direction	₽	Cutting Force	>>>	Speed		Blade
	Reverse		100gfs		15cm/s		45°
	Temperature	\bigcirc	Time	₩	Press Pressure		Peel
	150°C/302°F		10 seconds		Medium	-	Cool

NB: The plotter machine settings should be adjusted based on the age and brand of the machine.

HOW TO USE

- 1. Cut your design in reverse on a plotter machine.
- 2. Weed out excess film.

- 4. Apply medium and even pressure across your transfer.
- 5. Press for 10 seconds.
- 6. Peel the release liner when it is Cool.

3. Set a heat press to 150°C.6. Peel the releaseNB: We highly recommend performing a test before proceeding with standard production.

WASHING CONDITIONS Washing Machine: LG Drum / Detergent: Persil Liquid

Washing	Water Temp.	Tumble Dry	A Iron	Bleach
Standard	60°C	Available on low setting	Inside Out	Not Allowed

NB: It is recommended to wait at least 24hours after the heat pressing before a first washing.

STORAGE CONDITIONS

- * Temperature: Less than 25°C (± 3°C)
- * Relative Humidity: 40% (±20%)
- * Keep out of direct sunlight.
- * Shelf life: 1 year from manufacturing date

SUITABLE FOR

- * 100% Cotton or 100% Polyester
- * Mixtures of polyester/cotton
- * Acrylic and similar fabrics
- * Not suitable for Nylon or Coated Fabrics



Manufacturer of HTV and DTF Film

DAE HA CO., LTD. Main Office: 9F, 10F Daeha Bldg. 499 Gangseo-ro, Gangseo-gu Seoul 07523 Korea Phone: 82 2 2675 2758 I Email: info@garmentfilms.com I Web: www.garmentfilms.com

