TECHNICAL DATA SHEET

METALLIC PUFF PU

• Product Code: DFU

PRODUCT INFORMATION

Make your design as 3D and voluminous by Dae Ha Puff PU.

- Three-dimensional and voluminous effect.
- Thin foil film expands under heat pressure.
- Expressing metallic luster colors.
- Metallic Puff PU is suitable for Stretchable fabric.
- Various metallic colors are available.
 - Easy to cut and weed.

MATERIAL SPECIFICATION

- * Composition: Foil
- * Adhesive carrier
- * Thickness: 125 \pm 10 μ m
- * Standard roll size: 500mm x 50M

CUTTING & TRANSFER CONDITIONS Plotter Machine: GCC Jaguar IV / Mimaki CJV150 75

| Я | Cut Direction | ₽ | Cutting Force | >>> | Speed | Blade |
|-------|------------------------|-----------------------------------|---|---------------------|----------------|-------|
| | Reverse | | 100gfs | | 15cm/s | 45° |
| | Temperature | \bigcirc | Time | ₩ | Press Pressure | Peel |
| 135°C | 2~140°C / 275°F ~284°F | 1 ^s 2 nd | ^{.t} press: 10 sec. press: 3 ~ 5 sec. | | Medium | Warm |

NB: The plotter machine settings should be adjusted based on the age and brand of the machine.

HOW TO USE

- 1. Cut your design in reverse on a plotter machine.
- 2. Weed out excess film.
- 3. Set a heat press to 135°C~140°C.

- 5. Press for 10 seconds.
- 6. Tap the surface evenly for about 5 seconds.
- 7. Peel the release liner when it is Warm.
- 4. Apply medium and even pressure across your transfer. 8.
- Receive release lifer when it is warm.
 Cover the surface and press it for 3~5 seconds again.
- NB: We highly recommend performing a test before proceeding with standard production. Depending on the transfer temperature and time, the surface gloss may fade.

■ WASHING CONDITIONS Washing Machine: LG Drum / Detergent: Persil Liquid

| Washing | Water Temp. | Tumble Dry | A Iron | Bleach |
|---------|-------------|------------|------------|-------------|
| Wool | 40°C | Avoid | Inside Out | Not Allowed |

NB: It is recommended to wait at least 24hours after the heat pressing before a first washing.

STORAGE CONDITIONS

- * Temperature: Less than 25°C (±3°C)
- * Relative Humidity: 40% (±20%)
- * Keep out of direct sunlight.
- * Shelf life: 1 year from manufacturing date



SUITABLE FOR

- * 100% Cotton or 100% Polyester
- * Mixtures of polyester/cotton
- * Acrylic and similar fabrics
- * Not suitable for Nylon or Coated Fabrics



Manufacturer of HTV and DTF Film

DAE HA CO., LTD.

Main Office: 9F, 10F Daeha Bldg. 499 Gangseo-ro, Gangseo-gu Seoul 07523 Korea Phone: 82 2 2675 2758 I Email: info@garmentfilms.com I Web: www.garmentfilms.com