

RALEIGH PLANK


Prestige
waterproof flooring




Overall Thickness: 2.5 mm
Installation Method: Glue/Float
Warranty: 20 Year Residential | 10 Year Commercial

6" x 48"


COLORS




Buckeye
PRES8204DB




Carriage House
PRES147-32DB




Gunstock
PRES3365DB




Haywood
PRES437-1DB




Oak View
PRES312-30DB




Pewter
PRES4012DB




Redwood
PRES252-12DB



Saddle
PRES3366DB




Wake
PRES224-25DB



Yates Mill
PRES178-23DB

Top Layer:
Anti-Bacterial UV Cured Ceramic-Reinforced
Polyurethane

Wear Layer:
0.5 mm (20 mil)



RALEIGH PLANK

TECHNICAL DATA

2.5mm Glue Down Flooring

Nominal Dimensions: 6" x 48" x 2.5mm Planks

Wear Layer Thickness: 20 mil (0.020")

Finish: Anti-Bacterial UV Cured Ceramic-Reinforced Polyurethane

ASTM F1700 – Solid Vinyl Tile: Class III, Type B

ASTM E648 (NFPA 253) – Critical Radiant Flux: Class 1, > 0.45 W/cm²

ASTM E662 (NFPA 258) – Smoke Density: Passes, < 450

CAN/ULC-S102.2 – Surface Burning: 30 Flame Spread Rating | 250 Smoke Developed Classification

ASTM D2047 – Static Coefficient of Friction: > 0.60

ASTM F970 – Static Load Resistance: Passes less than .005" Indentation after 250 psi

ASTM F970 – Static Load Resistance (Modified): Passes less than .005" Indentation after 2,000 psi

ASTM F925 – Chemical Resistance: Excellent with chemicals listed in standard.

ASTM F1515 – Light Stability: Excellent, E < 8

ASTM F1914 – Residual Indentation: Excellent, < 8% after 24 hour recovery

ASTM F2199 – Dimensional Stability: Excellent, < 0.020" per linear foot

Acclimation Time: 48 Hours, See installation instructions for details

Service & Storage Temperature: 65° - 85° F, See installation instructions for details