

JHH TRADING PTY LTD

TEST REPORT

SCOPE OF WORK

Wood Plastic Composite Decking

REPORT NUMBER

231130009SHF-001

TEST DATE(S)

2023-11-30 - 2023-12-12

ISSUE DATE

2023-12-14

PAGES


5

DOCUMENT CONTROL NUMBER

LFT-APAC-SHF-OP-10k(September 1, 2022)

© 2022 INTERTEK

Intertek Testing Services Shenzhen Ltd. Shanghai Fengxian Branch



Test Report

Statement

- 1.This report is invalid without company's special seal for testing on the assigned page.
- 2.This report is invalid without an authorized person's signature.
- 3.This report is invalid if altered.
- 4.Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Don't copy this report in partial without any official approval in written by our company. This report is invalid without re-stamping the special seal for testing in copying report.
- 5.This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample(s) tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.
- 6.Except for the obligation, responsibility and liability (if any) for the appropriateness and professionalism of afore-mentioned testing itself within the scope and amount of the testing fee received, Intertek does not and will not accept any other obligation or liability.
- 7.If the Client has any questions about the test results, Intertek B&C should be informed within the storage period of the samples. The sample storage period ends 5 working days after the official report issue date. Samples of certification program are retained for the period required by the certification rules. The samples storage period shall be calculated according to the issue date of the original report in the case of quoting results and modifying reports.
- 8.Intertek B&C will service this report for the entire test record retention period. The test record retention period ends 6 years after this report original issue date. The test record retention period for certification program is 10 years. Test records and other pertinent project documentation will be retained for the entire test record retention period.
- 9.The report was digital signed by Shang Hai, Intertek Group plc, please using Adobe Acrobat Reader to verify the authenticity.



Test Report

Issue Date: 2023-12-14 Intertek Report No. 231130009SHF-001
Applicant: JHH TRADING PTY LTD
Address: 4 SEISMIC COURT ROWVILLE VICTORIA VIC 3178 AUSTRALIA
Attn: Guangzhou Li
Manufacturer: Nanjing Jufeng Advanced Materials Co., Ltd.
Address: NO.20.FEIYING ROAD BINJIANG ECONOMIC DEVELOPMENT ZONE JIANGNING DISTRICT, NANJING
Test Type: Performance test, samples provided by the applicant.

Product Information

Product Name	Wood Plastic Composite Decking	Brand	JUFENG
Sample Description	Good Condition	Sample Amount	6 pcs
		Received Date	2023-11-27
Sample ID	Model	Specification	
S231130009SHF.002	138K23	/	

Test Methods And Standards

Test Standard	AS 4586-2013/Amdt 1-2017 Appendix A
Specification Standard	/
Test Conclusion	The samples were tested according to the above standards, and the results are shown in the following page.

Note:

1.This report does not involve sampling. The report only reflects conformity of the tested items of the samples provided by the testing applicant. Representativeness and authenticity of the submitted samples are responsibilities of the testing applicant.

Report Authorized


Sally Xie Roger Chen
Name: Sally Xie Name: Roger Chen
Title: Reviewer Title: Project Engineer

Test Report

Issue Date: 2023-12-14

Intertek Report No. 231130009SHF-001

Test Items, Method and Results:

Test Item: Wet Pendulum Test
 Test Method: AS 4586-2013/Amdt 1-2017 Appendix A
 Conditioning: Condition the test specimens at (23 ± 2)°C and (50 ± 5)% relative humidity for 48 hours
 Test Temperature: 23 °C
 Slider: Slider 55
 Test Surface: Wet condition
 Test direction: 0°= parallel to length direction
 45°= angle of 45° with length direction or width direction
 90°= parallel to width direction

Test Item	Test Method	Test Result		Class
		Direction	Pendulum SRV	
Wet pendulum test	AS 4586-2013 Appendix A	0°	55	P5
		45°	65	
		90°	66	

Note:

1. Class based on the lowest result of three directions.
2. Test surface and directions were included in Appendix A of this report.

AS 4586 Wet Pendulum Test Classification of Pedestrian Surface Materials

Class	Pendulum SRV	
	Slider 96	Slider 55
P5	>54	>44
P4	45-54	40-44
P3	35-44	35-39
P2	25-34	20-34
P1	12-24	<20
P0	<12	/




Test Report

Issue Date: 2023-12-14

Intertek Report No. 231130009SHF-001

Appendix A: Sample Received Photo



Test surface



Back view



Section view

Revision:

NO.	Date	Changes
231130009SHF-001	2023-12-14	First issue

