



Salt Guard

Vertical & Horizontal Surfaces

TECHNICAL DATA SHEET

Silane / Siloxane water repellent provides protection from damage caused by road salt, ice, rain and snow.

Product Codes

LC	1Q → 2 Gal	SP-1004
	1Q → 5 Gal	SP-1005
Ready to Use	1 Gal	SP-1006
	5 Gal	SP-1007

Description

Salt Guard is the best protection from damage caused by road salt, ice, rain and snow. Formulated with Micro-Lok™ technology, Salt Guard creates a micro-molecular chemical and mechanical bond between the Salt Guard chemicals and the surface it has been applied to, preventing moisture from penetrating the surface. Salt Guard also prevents cracking and breaking of wood and masonry caused by continuous freeze/thaw cycles.

Features

- Resists damage from ice melt products
- Prevents damage from salt
- Not affected by weathering or UV light
- Single or multiple coat application
- V.O.C. compliant
- Contains no known carcinogens
- Breathable – does not trap moisture
- Can be used in cold temperature applications
- Will NOT yellow or turn cloudy
- UV protectant

Benefits

- Penetrates deep – Perfect for use on sidewalks, driveways and patios
- Apply prior to using “Ice Melt” for easy ice and snow removal
- Can be used on green, newly poured concrete
- Great winterizing agent – Protects all surfaces from icing and salt damage
- Easy to use – Same day, two coat application using a hand pump garden sprayer

Test Panel

Always apply material to a mock wall or test panel. Test wall or actual surface area to determine acceptable color, surface porosity, application rates and methods before starting application.

Coverage Rates* (Theoretical)

Substrate	Sq Ft / Gallon
Brick Surfaces	70-140
Stone Surfaces	70-140
Concrete Surfaces	70-140
Wood Decking	250
Sidewalks	125
Salt Water Pool Deck	100-125

**Extremely porous surfaces may require multiple coats*

Satisfaction Guarantee

We guarantee that you will be satisfied with our products. If you are unsatisfied, we will be happy to replace the product or issue a refund. See Rainguard.com for details.

Dilution

Add clean water to concentrate ONLY
If product is Ready To Use - DO NOT DILUTE

Rainguard® Salt Guard





How to Apply

1. Salt Guard should be applied using a hand pumped garden sprayer (do not atomize) or low-pressure airless spray equipment.
2. If using airless spray equipment we recommend a spray tip size of .035 to .051. Spray head should be held 8 to 12 inches from the surface so that the flood coat runs down the wall approximately 6-12 inches below the point of application.
3. Avoid application in windy weather.
4. Trigger gun off at the end of each pass to avoid using excessive materials. Stop all applications only at corners, joints, seams, or edges.
5. Multiple coats may be applied. Whiting or yellowing will not occur.

and mold and mildew, etc. All cracks should be pointed or caulked. All voids, beeholes, masonry surface defects and openings such as conduits, pipes, drains, door frames, vents, air conditioner openings, electrical openings, control joints, or any dissimilar materials should be repaired using urethane or other approved patching.

Do not apply to surfaces if moisture content is greater than 15% as measured with an electronic moisture meter. Do not apply materials in climates where freezing temperatures have existed prior to application. Allow adequate time for surfaces to thaw. Establish that air, surface, and material temperatures are above 40°F (4.4°C) and at least 5°F above the dew point prior to painting. Do not apply at temperatures below 40°F when temperatures are expected to drop below 40°F within 48 hours of application. Do not apply if rain, snow, or lower temperatures are expected within 48 hours. Do not apply if relative humidity is greater than 90%.

Store materials in a well-protected area at 45°-90°F. Avoid freezing temperatures, direct sunlight, & moisture. Keep away from heat sources.

Precautions & Limitations

All surfaces to be coated should be clean of any dirt and grime, efflorescence, lime run, form oils and release agents, grease, mud, excess mortar,

Test Data

Wind Driven Rain	ASTM E-514-86., 98.7% Leak Red
Water Pen Fed Spec	SS-W-110C, 75% Min Req, 96.8 Leak Red Chloride Ion Intr
Salt Pounding NCHRP	No. 244 Series IV - 95% Red No. 244 Series II - 83% Red
Water Abs CMU ASTM C140-75	98.6% Effective
Water Vapor Trans ASTM D-1653-71	100% Vapor Perm
Water Repellency ASTM C67-87	98.6% Effective
Weathering ASTM G-53	3,500 Hours - No Change
Surface Burning ASTM E84	Flame Spread 0, Smoke Development 0

Technical Data

Material Type	Silane/Siloxane
Active Content	100%
Volume Solids	40 or 80%(Depends on Dilution)
Color of Material	Milky White
Odor	Slight Odor
V.O.C.	0 g/L V.O.C. Compliant
Flash Point	Non-Flammable
pH Value	6
Viscosity	9.6 Seconds No. 4 Ford Cup
Weight	Approximately 8.7 lbs./Gal.
Surface Dry/Recoat	Approx 1 Hour
Full Chemical Cure	5 to 7 days



Disclaimer

Rainguard Brands, LLC guarantees that this product is free from manufacturing defects and complies with our published specifications. In the event that the buyer proves that the goods received do not conform to these specifications or were defectively manufactured, the buyer's remedies shall be limited to either the return of the goods and repayment of the purchase price or replacement of the defective material at the option of the seller. Rainguard Brands, LLC makes no other warranty, expressed or implied, and all warranties of merchantability and fitness for a particular purpose are hereby disclaimed. Manufacturer or seller shall not be liable for prospective profits or consequential damages resulting from the use of this product. Manufacturer shall not be liable for material used outside of its shelf life. For product dating, please refer to the batch number on the product or contact Rainguard Brands, LLC.

Surface conditions and application variables are out of the control of Rainguard Brands, LLC. As such, the applicator agrees to: Follow recommended application instructions, acknowledge limitations outlined in this technical data sheet, contact the manufacturer in the event there any uncertainties, perform a test panel to confirm fit and finish before any general application. The data on this sheet represents typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. Rainguard Brands assumes no obligation or liability for use of this information.

<<END>>



Rainguard® Salt Guard

