

# Which Modelling Material to Choose?

## Modelling selection Guide

Suitable for:	Kiln Firing Required	Air Drying	Can Be Painted?	Storage	Suitability and Uses (Suggestion Only)
Earthenware Clay	 Bisque fire at 1000°C	 Will crumble if not bisque fired.	 After bisque firing can be painted with acrylic paint or glazed (see glaze instructions).	Keep airtight, will dry out	Models, Pots & Sculptures
Midfire & Stoneware					Tableware / Functional-ware, Models, Pots & Sculptures
Raku Clay					Raku Firing Techniques
School Clay					Models, Pots & Sculptures
Terracotta Clay					Models, Pots & Sculptures.
Earthenware Paper Clay					Fires Light Weight
OZ Clay		 Air dries overnight	 Can be decorated with acrylic paint.	Keep airtight, will dry out	Small Models, Pots, Sculptures & Ornaments
No Fire Clay					
DAS Modelling Clay		 Air dries overnight	 Can be decorated with acrylic paint.	Keep airtight, will dry out	Small Models, Pots, Sculptures & Ornaments
Air Drying Clay					
Magiclay (Paper Modelling Clay)		 Air dries overnight	 Can be decorated with acrylic paint.	Keep airtight, will dry out	Small Models, Jewellery, 3D Relief Elements
Porcelain (Potato) Clay					
Polymer Clay (Oven)	 Oven			Keep airtight, will dry out	Small Models & Jewellery
Plasticine / PlastiPlay		 Re-use: Does not harden		Keep airtight, will dry out	Models, Animation & Play
Claydough					Models & Sensory Play
Modroc / ArtRoc		 Air dries overnight	 Can be decorated with acrylic paint.	Store in a waterproof container.	Sculptures, Models & Masks
Paper Mix					Casting
Pottery Plaster					Models & Bowls
Sculpt-It					