



Low VOC Lettering Enamels

Low VOC oil based, high gloss enamels for interior or exterior use on metal, glass, wood, enamel receptive banners and vinyl, vehicle lettering, pinstriping and graphics.

Features & Benefits

- UV Resistant
- Single stroke coverage
- Outstanding hiding, durability, and fade resistance
- Superior flow characteristics assure the virtual absence of brush marks and provide a clean, sharp edge
- Excellent weathering properties
- Vibrant colors can be intermixed
- Intended for sign writing on storefronts, vehicles, or wherever fine lettering is desired.
- Dried to touch in 1-2 hours

Compatible Surfaces

- Chromatic 5004 Clear Vinyl Primer
- 4331010 Gloss Chromatic TiCote Clear Primer/Barrier
- 4331011 Flat Chromatic TiCote Clear Primer/Barrier

Optional Products

Hardeners: 4007 Hardener

Reducers: ZZ6000 Chromaflo Enhancer, ZZ6001 Low Temperature Reducer, ZZ6002 High Temperature Reducer

Additives: 4329500 Clear Flattening Paste (no more than 50%), Dana Color D406 Smith's Cream Blending Agent (no more than 10%)

Directions For Use



Surface Preparation:

- Apply over clean, dry surfaces which are free from wax, grease, dust, chalk, etc., and have been primed with the appropriate 1-Shot/Chromatic Primer.
- Prime most rigid plastics, (including polystyrene, PVCs and PVFs) with Chromatic 5004 Clear Vinyl Primer. Prime most flexible plastics, synthetics, (including vinyl, many awning materials and non-ERC prepared banner materials) as well as leather and faux leathers with Chromatic Ti-Cote Primer Barrier (4331010 Gloss/4331011 Flat)



Directions For Use (Continued)



Mix Ratios:

- Use only 1-Shot 6000 series reducers (ZZ6000, ZZ6001, ZZ6002).
- For brush applications, use only as much reducer or flow enhancer as needed to maintain desired flow characteristics and brush control.
- For spray and airbrush applications, use no more than 40% 1-Shot 6001 Low Temp Reducer.
- Do not reduce 1-Shot Lettering Enamels for roller applications.



Application:

Brush, roll, spray or airbrush



Drying Times:

Drying time is best when temperature is above 65°F. Between 50°F and 65°F, drying time is much slower. Paint will not completely dry below 50°F.

- Dry to touch: 1 to 2 hours
- Dry to handle: 5 hours
- Dry to recoat: 12 to 16 hours
- Pot Life with Hardener: 3 hours

Total Film Build:

None required. Color dependent.

Equipment Cleaning:

- Clean equipment with mineral spirits
- Clean brushes with 1-Shot 4004 Brush Cleaner

Technical Data:

VOC2.32-2.7
Theoretical Coverage.....817-920 square feet at 1 mil 100% transfer

Important:

To prevent the possibility of condensation during the coating application the surface temperature should be a minimum 5° above the dew point. If the surface temperature is too high the solvents will volatilize within the film, causing tiny vapor blisters or pinholes that usually leads to an early coating failure. When the ambient temperature is too high, the coating may cure on the surface and inhibit full cure of the underlying material and this will also lead to the formation of blisters and pinholes. To prevent above problems the temperature range has been established. The additives should be used when their properties are required.

The contents of this package may have to be blended with other components before the product can be used. Before opening the packages, be sure you understand the warning messages on the labels of all components, since the mixture will have the hazards of all its parts. Improper spray technique may result in a hazardous condition. Follow spray equipment manufacturer's instructions to prevent personal injury or fire. Follow directions for respirator use. Wear eye and skin protection. Observe all applicable precautions.

See Material Safety Data Sheet and Labels for additional safety information and handling instructions.

Emergency Medical or Spill Control Information:

US (412) 434-4515; CANADA (514) 645-1320; Mexico 01-800-00-21-400

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public. Products mentioned may be hazardous and should only be used according to directions, while observing precautions and warning statements listed on label. Statements and methods described are based upon the best information and practices known to Matthews Paint. Procedures for applications mentioned are suggestions only and are not to be construed as representations or warranties as to performance, results, or fitness for any intended use, nor does Matthews Paint warrant freedom from patent infringement in the use of any formula or process set forth herein. If you require technical assistance, please call us toll-free 800/323-6593.