

RUST-OLEUM®
INDUSTRIAL



TARMACOAT™

Versatile rapid curing floor paint

- Rain-proof and recoatable after just one hour
- Can be applied on slightly damp surfaces
- Excellent resistance to U.V. and weathering
- Water-based formulation, safe to use and virtually no odour
- Single pack, no mixing required

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

TARMACOAT™

DESCRIPTION

Very fast-drying multi-purpose single pack acrylic water-based paint for floors and paint marking.

RECOMMENDED USE

As a coating on asphalt, concrete, pavement, bitumen, on parking bays for short term or intermittent use, as line marking, on tennis courts, playgrounds and many more. Not suitable for garage floors. The product will cure sufficiently in approximately 24 hours to accept light traffic (bicycle, car, etc.). In instances where occasional heavy traffic may be expected, allow 48 hours before bringing the area back into service. Cold and damp weather can have a negative effect on drying times.

TECHNICAL DATA

Density:	1,3
Gloss Level:	Matt
Solids content in volume:	45 %
Solids Content in weight:	57 %

DRYING TIMES AT 20°C/RH 50%

Touch dry:	30 minutes
Dry to handle:	1 hour
Dry to recoat:	1 hour
Fully cured:	2 days

RECOMMENDED WET FILM THICKNESS

120 µm

RECOMMENDED DRY FILM THICKNESS

54 µm

THEORETICAL CONSUMPTION

4 - 8 m² per liter, depending on the type of surface.

PRACTICAL CONSUMPTION

Depending on the type of surface. On Tarmac, coverage is likely to be close to 4 m²/l.

SURFACE PREPARATION

Ensure the surface is clean, sound and dry (slightly damp is acceptable). Tarmacoat can be applied to existing paint providing all poorly bonded material is removed and glossy surfaces are dulled using abrasive paper. For concrete surfaces which are porous and/or have loose particles or powdering, first prime with Primer 44HS® or EpoxyShield Sealer 5220. For non-porous concrete prime with diluted NOXYDE®. For asphalt surfaces apply first a coat Tarmacoat™ 20% diluted with water.

DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS

Do not apply externally if rain or frost is forecast or if the temperature is below 10°C. Relative humidity below 85%.

APPLICATION & THINNING: BRUSH

Apply undiluted.

APPLICATION & THINNING: ROLLER

Apply by medium pile type roller. One coat is generally sufficient although a second coat may be necessary on very porous or very rough surfaces or when a better durable system is required. Apply undiluted.

CLEANING OF EQUIPMENT / SPILLS

Clean tools in warm soapy water before the product has started to cure.

REMARKS

Do not apply in areas which will be constantly under water.

SAFETY DATA

VOC level:	40 g/l
VOC readymix:	40 g/l
VOC category:	A/i
VOC limit:	140 g/l
Grenelle:	A+
Flashpoint:	Not flammable
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE

2 years from date of production in its sealed original packaging, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 29/04/2019

Available colours & pack sizes : Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer : The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu