

Pasty acrylic putty

Description

ISOMAT ACRYL STUCCO is a ready-to-use water based acrylic putty, suitable for stuccoing (skim coat puttying) in interior and exterior areas. It is very convenient in application and rubbing. It provides a flat and smooth final surface, ready for priming and painting.

Certified with the CE marking according to EN 13963 as a 3A jointing compound for gypsum plasterboards (bedding and finishing compound).

Fields of application

ISOMAT ACRYL STUCCO is ideal stuccoing surfaces of plaster, concrete, masonry, wood, gypsum board and cement board.

Technical data

Form:	pasty
Color:	white
Density:	1,65 ± 0,05 kg/l
Drying time:	1-2 h
Subsequent layer in:	2-3 h
Minimum application temperature:	+5°C
Adhesios strength	
to gypsum board:	0,35 N/mm ²
Resistance to cracking:	passed
Flexural strength:	300 N

Directions for use

1. Substrate

The substrate must be stable and free of dust, grease, loose particles etc.

Plastered wall may be repaired with UNICRET and UNICRET-FAST premixed mortars.

When the substrate is loose or crumbly it is recommended to stabilise it by priming it with the acrylic, micronized, water based primer PRIMER CLASSIC, thinned up to 50% with clean water.

2. Application

ISOMAT ACRYL STUCCO is applied by trowel using a dragging technique in two coats. The second coat follows after the first has dried.

After stuccoing, the final surface is smoothed out by sand paper in order to be primed and then painted.

Consumption

1,5 - 2,5 kg/m², depending on layer thickness.

Packaging

ISOMAT ACRYL STUCCO is supplied in plastic containers of 400 g and 800 g.

Shelf-life - Storage

12 months from production date if stored in original, unopened packaging, in temperature between +5°C and +35°C. Protect from direct sun exposure and frost.

Volatile organic compounds (VOCs)

According to the Directive 2004/42/CE (Annex II, table A), the maximum allowed VOC content for the product subcategory g, type WB is 30g/l (2010) for the ready to use product. The ready to use product ISOMAT ACRYL STUCCO contains max <30 g/l VOC.

ISOMAT ACRYL STUCCO



ISOMAT S.A.

17th km Thessaloniki – Ag. Athanasios
P.O. BOX 1043, 570 03 Ag Athanasios, Greece

13

3A - EN 13963

Reaction to fire: F

Flexural strength: 300 N

ISOMAT S.A.

BUILDING CHEMICALS AND MORTARS

MAIN OFFICES - FACTORY:

17th km Thessaloniki - Ag. Athanasios Road,
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece,
Tel.: +30 2310 576 000, Fax: +30 2310 722 475

www.isomat.net e-mail: info@isomat.net

The technical information and instructions supplied in this datasheet are based on the knowledge and experience of the Department of Research and Development of our company and on results from long-term applications of the product in practice. The recommendations and suggestions referring to the use of the product are provided without guarantee, since site conditions during the applications are beyond the control of our company. Therefore the user is responsible for confirming that the chosen product is suitable for the envisaged application. The present edition of this technical datasheet automatically cancels any previous one concerning the same product. | Edition: 08.9.20

