

## Pasty gypsum board putty - Joint compound

### Description

GB-COVER is a ready-to-use putty, suitable for stuccoing (skim coat puttying) and pointing of gypsum boards. It is very easy to use (application and rubbing). It provides a flat and smooth final surface, ready for priming and painting.

Certified with the CE marking, according to EN 13963, as a 3A jointing compound for gypsum plasterboards (bedding and finishing compound).

### Fields of application

GB-COVER is ideal for gypsum board stuccoing, whereas in combination with joint tapes, it is used as a joint compound for pointing and crack filling.

### Technical data

Form:	pasty
Color:	white
Density:	1.65 kg/l
Drying time:	1-2 h
Subsequent layer in:	2-3 h
Minimum application temperature:	+5°C
Adhesion strength:	0.3 N/mm <sup>2</sup>
Resistance to cracking:	Pass
Flexural strength:	150 N

### Directions for use

#### 1. Substrate preparation

The substrate must be stable and free of dust, grease, loose particles etc.

#### 2. Application

##### a) Stuccoing

GB-COVER is applied by trowel, using a dragging technique in two coats. The second coat is applied, after the first one has dried.

##### b) Pointing and crack filling

First, a self-sticking joint tape is placed along the joint or the crack. GB-COVER is applied on the dry and clean surface in two layers using a trowel. The second layer is applied, after the first one has dried. Alternatively, if the tape is not self-sticking, a GB-COVER layer is first applied along the joint or crack and, while it's still fresh, the tape is placed and pressed to get embedded to the joint compound. When the surface dries off, the second layer may follow. After stuccoing or pointing, the final surface is smoothed out by glass paper in order to be primed and then painted.

### Consumption

2.0-3.0 kg/m<sup>2</sup>, depending on the layer thickness.

### Packaging

GB-COVER is supplied in plastic containers of 7 kg and 20 kg.

### Shelf-life - Storage

12 months from production date, if stored in original, unopened packaging, at temperatures between +5°C and +35°C. Protect from direct sun exposure and frost.

# GB-COVER



## Volatile Organic Compounds (VOCs)

According to the Directive 2004/42/CE (Annex II, table A), the maximum allowed VOC content for the product subcategory g, type WB is 30 g/l (2010) for the ready-to-use product. The ready-to-use product GB-COVER contains a maximum of 30 g/l VOC.



**ISOMAT S.A.**

17<sup>th</sup> km Thessaloniki – Ag. Athanasios  
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece

12

3A - EN 13963

Reaction to fire: F

Flexural strength: 150 N

## ISOMAT S.A.

BUILDING CHEMICALS AND MORTARS

### MAIN OFFICES - FACTORY:

17th km Thessaloniki - Ag. Athanasios Road,  
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece,  
Tel.: +30 2310 576 000, Fax: +30 2310 722 475

[www.isomat.net](http://www.isomat.net) e-mail: [info@isomat.net](mailto:info@isomat.net)

The technical information and instructions supplied in this datasheet are based on the knowledge and experience of the Department of Research and Development of our company and on results from long-term applications of the product in practice. The recommendations and suggestions referring to the use of the product are provided without guarantee, since site conditions during the applications are beyond the control of our company. Therefore the user is responsible for confirming that the chosen product is suitable for the envisaged application. The present edition of this technical datasheet automatically cancels any previous one concerning the same product.

