

## Premium quality, water-based, enamel paint

### Description

Premium quality, new generation, water-based, enamel paint for wooden surfaces. It is suitable for both indoor and outdoor use. ISOLAC-AQUA is characterized by high flexibility and coverage. It has excellent resistance to weather, ageing and frequent washing and therefore it does not yellow. It has strong adhesion and is suitable for repainting surfaces coated with water-based or solvent-based enamel paints. It is almost odorless, it has excellent workability and dries quickly. It is available in gloss (ISOLAC-AQUA GLOSS) and in satin finish (ISOLAC-AQUA SATIN).

### Fields of application

ISOLAC-AQUA is used for indoor or outdoor applications, on new or old wood surfaces.

### Technical data

Colors:	white and 1950 selected (ISOMAT COLOR SYSTEM)
Type:	water-based enamel paint
Density:	1,25 kg/l (GLOSS), 1,30 kg/l (SATIN)
pH:	8-9 at +23°C
Opacity:	min 97 %
Whiteness:	min 95 %
Capillary water absorption:	0,05 kg/m <sup>2</sup> h <sup>0,5</sup>
Bond strength:	2,0 N/mm <sup>2</sup>
Viscosity (Poise):	15-20
Drying time:	1 h (in touch)
Recoating in:	6 h

### Cleaning of tools:

Remove as much paint as possible from the used tools before cleaning. Clean the tools thoroughly with water and detergent immediately after use.

### Directions for use

#### 1. Substrate

The substrate should be dry and free of grease, loose particles, dust etc., while any imperfections should be rubbed down with sandpaper. Priming with ISOLAC PRIMER AQUA, should follow, thinned up to 5-10% with clean water for application by brush or by roller and up to 20-30% for airless spray application.

#### 2. Application

Before using ISOLAC-AQUA, slightly stir its content and apply it in two layers either thinned by 5-10% with clean water for application by brush or by roller and up to 20-30% for airless spray application. The second coat is applied after the first coat has completely dried. Temperature during application and drying of the colour should be among +10°C and +35°C.

### Coverage

ISOLAC-AQUA covers 12 m<sup>2</sup>/l per coat, on previously prepared surfaces.

### Packaging

ISOLAC-AQUA is supplied in buckets of 0,75 and 2,5 l.

## Shelf-life - Storage

12 months from production date if stored in original, unopened packaging, in temperature between +5°C and +35°C. Protect from direct sun exposure and frost.

## Volatile organic compounds (VOCs)

According to the Directive 2004/42/CE (Annex II, table A), the maximum allowed VOC content for the product subcategory d, type WB is 130g/l (2010) for the ready to use product.

The ready to use product ISOLAC-AQUA contains max <130 g/l VOC.

**ISOMAT S.A.**  
BUILDING CHEMICALS AND MORTARS  
**MAIN OFFICES - FACTORY:**  
17th km Thessaloniki - Ag. Athanasios Road,  
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece,  
Tel.: +30 2310 576 000, Fax: +30 2310 722 475  
**www.isomat.net e-mail: info@isomat.net**