



Certified Archival Standards

Test Name	Targets	Test Methods
pH:	8.0 - 9.5 pH	TAPPI T 509 cold extraction
Lignin:	Negative/Kappa 5	ASTM D 1030, X5 or TAPPI 236
Reducible Sulfur:	< 0.0008%	TAPPI T 406
Iron:	< 150 ppm	TAPPI T-266
Copper:	< 6 ppm	TAPPI T-266
Alkaline Reserve:	3%	ASTM D 4988-89
Alum Rosin Sizing:	negative	ASTM D 549-88
Photographic Activity	negative	ISO 18916
Color Bleeding:	none	48 hr distilled water submersion
Color Retention:	< 5 points	TAPPI T 452
Flouresence	Negative	Black Light Reflectance
Dyes/Shade	Pigment Dyes	Match Shade of samples Delta "E" <2.0

www.Framebacks.com