

AMACO SUSPENDAID
(AP Non-Toxic)

AMACO SUSPENDAID with AMACO Brushing Glazes

Suspendaid is an anti-settling additive. It is used to change a brushing glaze (usually packaged in liquid form) to a closer workability of a dipping glaze (usually packaged in dry form). Upon doing that disregard the brushing glaze directions on the label and follow the following general directions.

- 1) ½ Pint (8 oz) Directions: A) Take out 2 oz. of glaze from the pint jar. B) Add 2 oz. of distilled water* and 1/2 tablespoon of Suspendaid. Mix thoroughly before using for dipping.
- 2) Pint (16 oz) Directions: A) Take out 4 oz. of glaze from the pint jar. B) Add 4 oz. of distilled water and 1 tablespoon of Suspendaid. Mix thoroughly before using for dipping.
- 3) Gallon Directions: A) Take 2 pints of glaze from gallon jar. B) Add 1 and ½ pints of distilled water and 6 oz. of Suspendaid. Mix thoroughly before using for dipping.
- 4) Dry 1 lb Directions: A) Add 1 pint (16 oz.) of distilled water to 1 lb. dry glaze. B) Add 2 and ½ tablespoon (1 oz.) of Suspendaid. Mix thoroughly before using for dipping.

Glazes vary in viscosity, therefore if you feel that your dipping glaze needs to be thinner, add a little more distilled water. If your glaze settles, then add a little more Suspendaid. With practice you will learn how much water and Suspendaid needs to be added for the dipping glaze consistency that you like.

25lb Dry glazes

If your glaze settles to the bottom of the bucket in a hard layer (hard-pans) thoroughly mix the glaze with a high-speed mixer for an additional 15 minutes. If it continues to hard-pan, AND your specific gravity is correct, add one cup (8 fl oz or 237 ml) of AMACO Suspendaid to the bucket of glaze, mix with a high-speed mixer for at least 10 minutes and let sit overnight.

10lb Dry glazes

If your glaze settles to the bottom of the bucket in a hard layer (hard-pans) thoroughly mix the glaze with a high-speed mixer for an additional 15 minutes. If it continues to hard-pan, AND your specific gravity is correct, add half a cup (4 fl oz or 188 ml) of AMACO Suspendaid to the bucket of glaze, mix with a high-speed mixer for at least 10 minutes and let sit overnight.