

# Ultra High NA SM Fiber

T-UHNA3

## Description

Ultra-high NA fluoride optical fiber provides excellent coupling efficiency to high NA waveguides and standard silica fibers. This range of fibers offers up to 0.35 NA.

## Specifications

Geometrical & Mechanical	
Clad Diameter	125 ± 1.0 µm
Coating Diameter	250 ± 20 µm
Core Diameter	1.8 µm
Coating Concentricity	<5.0 µm
Core-Clad Offset	≤0.5 µm
Coating Material	UV Cured, Dual Acrylate
Operating Temperature	-55 to 85 °C
Short-Term Bend Radius	≥12 mm
Long-Term Bend Radius	≥25 mm
Proof Test Level	≥100 kpsi (0.7 GN/m <sup>2</sup> )

Optical	
Numerical Aperture (nominal)	0.35
Operating Wavelength (nominal)	960 - 1600 nm
Mode Field Diameter	2.6 ± 0.3 µm @ 1100 nm 3.3 ± 0.3 µm @ 1310 nm 4.1 ± 0.3 µm @ 1550 nm
Second Mode Cutoff	900 ± 50 nm
Bend Loss @ 1100 nm (100 Turns, 25 mm Radius)	<0.001 dB
Bend Radius for 0.05 dB per 100 Turns @ 1100 nm	Much less than LTBR

