

Product Data Sheet

Water-Based Wood Coating

2K Acrylic Polyurethane Primer

General Description

This true two-component, white, acrylic, polyurethane primer is designed to be used in interior applications where extreme chemical and moisture resistance is required. Unlike most competitive polyurethanes, this is not a polyurethane dispersion/modified acrylic topcoat. It requires a 10-15%-by-weight mixture with CW-4002 Hardener (based on aliphatic isocyanate) to provide a fully crosslinked film.

Physical Properties

| , | |
|------------------------|------------------------------|
| Vehicle Type | OH functional acrylic polyol |
| Solids by Volume | 43.44 (+/-1%) |
| Solids by Weight | 54.57 (+/-1%) |
| VOC (4:1 minus exempt) | 97.10 g/l |
| VOC (4:1 as supplied) | 47.26 g/l |
| Specific Gravity | 1.24 |
| Viscosity | 47-53 sec Zahn #3 |

Application

| Application Method | May be sprayed with conventional, airless, and air-assisted airless equipment. |
|--------------------------|---|
| Mixing Instructions | Mix 10-15% by weight with CW-4002 Hardener under agitation. May be mixed with water as needed. Pot life is 3-4 hours. |
| Substrate Preparation | The surface must be clean, dry and free of grease, oil, dirt, fingerprints and any other contamination to ensure proper adhesion. Remove any loose or peeling paint. Sand base coat with 320-400 grit sandpaper. When used as a sealer, use 220-320 grit sandpaper between coats. May be applied over acrylic, nitrocellulose and UV basecoat. Test for adhesion and compatibility before full-scale application. |
| Application Instructions | IMPORTANT: Mix well using a power agitator prior to application. Upon application, the temperature of the product, substrate and coating should be above 65°F. Apply up to 3 coats, allowing enough drying time between coats. |
| Coverage | Approx. 758 square feet per gallon at 1 dry mil. @ 100% transfer efficiency. Actual coverage may vary depending on application technique, equipment and weather conditions. |

Curing/Drying Time PropertiesForce Dry TimeAir Drying Time (77°F, 50% Humidity)Flash-Off10 minDust/Tack Free20-25 minNo More Than 120°F30 minSand and Recoat45-60 minPackageovernight

Available Products

CW-1107 (White)

Features/Advantages

- High build
- Excellent chemical resistance
- Excellent moisture resistance
- Meets or exceeds KCMA performance specifications
- Easy to sand

Recommended for:

- High performance interior wood applications
- Concrete
- Masonry
- Plastic

Safety/Cleanup

Please read the product Safety Data Sheet and product label before using product. Application tools must be cleaned with water after use. Dispose of any leftover materials in accordance with local, state or federal regulations.



CIC COATINGS | 2935 Almeta Lane | McKinney, TX 75069 | Ph: 972-384-1280 |